

ASME B31G-2009
(Revision of ASME B31G-1991)

Manual for Determining the Remaining Strength of Corroded Pipelines

**Supplement to ASME B31 Code for
Pressure Piping**

AN AMERICAN NATIONAL STANDARD



**The American Society of
Mechanical Engineers**



ASME B31G-2009
(Revision of ASME B31G-1991)

Manual for Determining the Remaining Strength of Corroded Pipelines

**Supplement to ASME B31 Code for
Pressure Piping**

AN AMERICAN NATIONAL STANDARD



Date of Issuance: October 30, 2009

The next edition of this Manual is scheduled for publication in 2012. There will be no addenda issued to this edition.

ASME issues written replies to inquiries concerning interpretations of technical aspects of this Manual. Interpretations, Code Cases, and errata are published on the ASME Web site under the Committee Pages at <http://cstools.asme.org> as they are issued.

ASME is the registered trademark of The American Society of Mechanical Engineers.

This code or standard was developed under procedures accredited as meeting the criteria for American National Standards. The Standards Committee that approved the code or standard was balanced to assure that individuals from competent and concerned interests have had an opportunity to participate. The proposed code or standard was made available for public review and comment that provides an opportunity for additional public input from industry, academia, regulatory agencies, and the public-at-large.

ASME does not “approve,” “rate,” or “endorse” any item, construction, proprietary device, or activity.

ASME does not take any position with respect to the validity of any patent rights asserted in connection with any items mentioned in this document, and does not undertake to insure anyone utilizing a standard against liability for infringement of any applicable letters patent, nor assumes any such liability. Users of a code or standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, is entirely their own responsibility.

Participation by federal agency representative(s) or person(s) affiliated with industry is not to be interpreted as government or industry endorsement of this code or standard.

ASME accepts responsibility for only those interpretations of this document issued in accordance with the established ASME procedures and policies, which precludes the issuance of interpretations by individuals.

No part of this document may be reproduced in any form,
in an electronic retrieval system or otherwise,
without the prior written permission of the publisher.

The American Society of Mechanical Engineers
Three Park Avenue, New York, NY 10016-5990

Copyright © 2009 by
THE AMERICAN SOCIETY OF MECHANICAL ENGINEERS
All rights reserved
Printed in U.S.A.

CONTENTS

Foreword	iv
Committee Roster	v
Correspondence With the B31 Committee	vi
1 Introduction	1
2 Evaluation Methods	5
3 Tables of Allowable Length of Corrosion	6
Figures	
1.12-1 Corrosion Pit Interaction Distances	7
1.13-1 Helically Oriented Corrosion Pattern	7
2.1-1 Corrosion Parameters Used in Analysis	8
Tables	
3-1 Values of L for Pipe Sizes \geq NPS 2 and $<$ NPS 6	9
3-1M Values of L for Pipe Sizes \geq 60 mm and $<$ 168 mm O.D.	9
3-2 Values of L for Pipe Sizes \geq NPS 6 and $<$ NPS 10	10
3-2M Values of L for Pipe Sizes \geq 168 mm and $<$ 273 mm O.D.	11
3-3 Values of L for Pipe Sizes \geq NPS 10 and $<$ NPS 16	12
3-3M Values of L for Pipe Sizes \geq 273 mm and $<$ 406 mm O.D.	13
3-4 Values of L for Pipe Sizes \geq NPS 16 and $<$ NPS 20	14
3-4M Values of L for Pipe Sizes \geq 406 mm and $<$ 508 mm O.D.	15
3-5 Values of L for Pipe Sizes \geq NPS 20 and $<$ NPS 24	16
3-5M Values of L for Pipe Sizes \geq 508 mm and $<$ 610 mm O.D.	17
3-6 Values of L for Pipe Sizes \geq NPS 24 and $<$ NPS 30	18
3-6M Values of L for Pipe Sizes \geq 610 mm and $<$ 762 mm O.D.	19
3-7 Values of L for Pipe Sizes \geq NPS 30 and $<$ NPS 36	20
3-7M Values of L for Pipe Sizes \geq 762 mm and $<$ 914 mm O.D.	21
3-8 Values of L for Pipe Sizes \geq NPS 36 and $<$ NPS 42	22
3-8M Values of L for Pipe Sizes \geq 914 mm and $<$ 1 066 mm O.D.	23
3-9 Values of L for Pipe Sizes \geq NPS 42 and $<$ NPS 48	24
3-9M Values of L for Pipe Sizes \geq 1 066 mm and $<$ 1 219 mm O.D.	27
3-10 Values of L for Pipe Sizes \geq NPS 48 and $<$ NPS 52	30
3-10M Values of L for Pipe Sizes \geq 1 219 mm and $<$ 1 320 mm O.D.	33
3-11 Values of L for Pipe Sizes \geq NPS 52 and $<$ NPS 56	36
3-11M Values of L for Pipe Sizes \geq 1 320 mm and $<$ 1 422 mm O.D.	39
3-12 Values of L for Pipe Sizes \geq NPS 56 Through NPS 60	42
3-12M Values of L for Pipe Sizes \geq 1 422 mm Through 1 524 mm O.D.	45

FOREWORD

It has been recognized within the pipeline industry that some sections of high-pressure pipelines, particularly those with long service histories, may experience corrosion. It has also been recognized, through theoretical analysis, scientific research and testing, and industry operating experience, that some amount of metal loss due to corrosion can be tolerated without impairing the ability of the pipeline to operate safely. In 1984, ASME published the first edition of the B31G Manual for Determining the Remaining Strength of Corroded Pipelines. The B31G document provided pipeline operators with a simplified evaluation method based on the results of analysis and tests. The application of B31G has enabled pipeline operators to reliably determine safe operating pressure levels for pipe affected by corrosion, and to determine whether repairs are necessary in order to continue operating safely.

B31G continued to be reissued by ASME with only minor revisions over time, although other corrosion evaluation methods had evolved since B31G's initial publication. A majority of these other methods are based on the same theoretical model from which the original B31G method was derived, but may offer some refinement in accuracy. Subsequently, an effort was undertaken to update the B31G document to recognize certain other corrosion evaluation methods that have proven sound and that have seen successful use in the pipeline industry. Incorporation of these other methods into a recognized Code document provides the pipeline operator or other user with a formalized framework within which to use such methodologies, as well as a wider range of codified technical options with which to make an evaluation. This 2009 revision of B31G reflects those objectives. ASME B31G-2009 was approved by the American National Standards Institute (ANSI) on July 10, 2009.

ASME B31 COMMITTEE

Code for Pressure Piping

(The following is the roster of the Committee at the time of approval of this Standard.)

COMMITTEE OFFICERS

M. L. Nayyar, *Chair*
K. C. Bodenhamer, *Vice Chair*
N. Lobo, *Secretary*

COMMITTEE PERSONNEL

R. J. T. Appleby, ExxonMobil Upstream Research Co.
C. Becht IV, Becht Engineering Co.
A. E. Beyer, Fluor Enterprises, Inc.
K. C. Bodenhamer, Epco, Inc.
C. J. Campbell, Air Liquide
J. S. Chin, TransCanada Pipeline U.S.
D. D. Christian, Victaulic
D. L. Coym, Worley Parsons
R. P. Deubler, Fronek Power Systems, LLC
J. A. Drake, Spectra Energy Transmission
P. D. Flenner, Flenner Engineering Services
J. W. Frey, Stress Engineering Service, Inc.
D. R. Frikken, Becht Engineering Co.
R. A. Grichuk, Fluor Corp.
R. W. Haupt, Pressure Piping Engineering Associates, Inc.
L. E. Hayden, Jr., Consultant
B. P. Holbrook, Babcock Power, Inc.
G. A. Jolly, Vogt Valves/Flowserve Corp.

N. Lobo, The American Society of Mechanical Engineers
W. J. Mauro, American Electric Power
J. E. Meyer, Louis Perry & Associates, Inc.
E. Michalopoulos, Management Authority of West Macedonia
M. L. Nayyar, Bechtel Power Corp.
R. G. Payne, Alstom Power, Inc.
J. T. Powers, Worley Parsons
E. H. Rinaca, Dominion Resources, Inc.
M. J. Rosenfeld, Kiefner & Associates, Inc.
R. J. Silvia, Process Engineers and Constructors, Inc.
W. J. Sperko, Sperko Engineering Services, Inc.
F. W. Tatar, FM Global
K. A. Vilminot, Black & Veatch
A. L. Watkins, First Energy Corp.
K. H. Wooten, ConocoPhillips Pipe Line Co.
W. J. Koves, *Ex-Officio*, UOP LLC
A. P. Rangus, *Ex-Officio*, Bechtel
R. A. Appleton, *Contributing Member*, Refrigeration Systems Co.

B31 MECHANICAL DESIGN TECHNICAL COMMITTEE

W. J. Koves, *Chair*, UOP LLC
G. A. Antaki, *Vice Chair*, Becht Nuclear Services
C. E. O'Brien, *Secretary*, The American Society of Mechanical Engineers
C. Becht IV, Becht Engineering Co.
J. P. Breen, Becht Engineering Co.
N. F. Consumo, GE Energy (IGCC) NPI
J. P. Ellenberger
D. J. Fetzner, BP Exploration Alaska, Inc.
J. A. Graziano, Tennessee Valley Authority
R. W. Haupt, Pressure Piping Engineering Associates, Inc.

B. P. Holbrook, Babcock Power, Inc.
G. D. Mayers, Alion Science & Technology
T. Q. McCawley, TQM Engineering, PC
R. J. Medvick, Swagelok
J. C. Minichiello, Bechtel National, Inc.
A. W. Paulin, Paulin Research Group
R. A. Robleto, Senior Technical Advisor
M. J. Rosenfeld, Kiefner & Associates, Inc.
G. Stevick, Berkeley Engineering & Research, Inc.
E. A. Wais, Wais and Associates, Inc.
E. C. Rodabaugh, *Honorary Member*, Consultant

CORRESPONDENCE WITH THE B31 COMMITTEE

General. ASME Standards are developed and maintained with the intent to represent the consensus of concerned interests. As such, users of this Standard may interact with the Committee by requesting interpretations, proposing revisions, and attending Committee meetings. Correspondence should be addressed to

Secretary, B31 Committee
The American Society of Mechanical Engineers
Three Park Avenue
New York, NY 10016-5990

Proposing Revisions. Revisions are made periodically to the Standard to incorporate changes that appear necessary or desirable, as demonstrated by the experience gained from the application of the Standard. Approved revisions will be published periodically.

The Committee welcomes proposals for revisions to this Standard. Such proposals should be as specific as possible, citing the paragraph number(s), the proposed wording, and a detailed description of the reasons for the proposal, including any pertinent documentation.

Interpretations. Upon request, the B31 Mechanical Design Technical Committee will render an interpretation of any requirement of the Standard. Interpretations can only be rendered in response to a written request sent to the Secretary of the B31 Committee.

The request for interpretation should be clear and unambiguous. It is further recommended that the inquirer submit his/her request in the following format:

Subject:	Cite the applicable paragraph number(s) and the topic of the inquiry.
Edition:	Cite the applicable edition of the Standard for which the interpretation is being requested.
Question:	Phrase the question as a request for an interpretation of a specific requirement suitable for general understanding and use, not as a request for an approval of a proprietary design or situation. The inquirer may also include any plans or drawings that are necessary to explain the question; however, they should not contain proprietary names or information.

Requests that are not in this format will be rewritten in this format by the Committee prior to being answered, which may inadvertently change the intent of the original request.

ASME procedures provide for reconsideration of any interpretation when or if additional information that might affect an interpretation is available. Further, persons aggrieved by an interpretation may appeal to the cognizant ASME Committee or Subcommittee. ASME does not "approve," "certify," "rate," or "endorse" any item, construction, proprietary device, or activity.

Attending Committee Meetings. The B31 Committee regularly holds meetings, which are open to the public. Persons wishing to attend any meeting should contact the Secretary of the B31 Committee.

MANUAL FOR DETERMINING THE REMAINING STRENGTH OF CORRODED PIPELINES

1 INTRODUCTION

1.1 Scope

This document is intended solely for the purpose of providing guidance in the evaluation of metal loss in pressurized pipelines and piping systems. It is applicable to all pipelines and piping systems within the scope of the transportation pipeline codes that are part of ASME B31 Code for Pressure Piping, namely: ASME B31.4, Pipeline Transportation Systems for Liquid Hydrocarbons and Other Liquids; ASME B31.8, Gas Transmission and Distribution Piping Systems; ASME B31.11, Slurry Transportation Piping Systems; and ASME B31.12, Hydrogen Piping and Pipelines, Part PL. Where the term *pipeline* is used, it may also be read to apply to piping or pipe conforming to the acceptable applications and within the technical limitations discussed below.

1.2 Acceptable Applications

The application of this document is limited to the evaluation of wall loss in metal pipe within the following limitations:

- (a) metal loss in pipelines located below ground, above ground, or offshore
- (b) metal loss due to external or internal corrosion
- (c) metal loss produced by grinding where used to completely remove mechanical damage, cracks, arc burns, manufacturing defects, or other defects from the pipe surface
- (d) metal loss in field bends, induction bends, and elbows
- (e) metal loss that incidentally affects longitudinal or helical electric seam welds or circumferential electric welds of sound quality and having ductile characteristics, provided workmanship flaws are not present in sufficiently close proximity to interact with the metal loss
- (f) metal loss of any depth with respect to the pipe wall, except that due consideration shall be given to the accuracy of measurements and effective corrosion rates when the depth of metal loss exceeds 80% of the actual pipe wall dimension
- (g) metal loss in new pipe where allowed by the applicable code of construction

(h) metal loss in pipe material having ductile fracture initiation characteristics [see paras. 1.7(e) and (f)] unless using a Level 3 assessment in accordance with paras. 2.2(b) and 2.3

(i) metal loss in pipe operating at temperatures above ambient within the range of operating temperature recognized by the governing standard, and provided material strength properties at temperature are considered

(j) metal loss in pipe operating at any level of allowable design hoop stress [see paras. 1.4(a) and (b) for additional considerations]

(k) metal loss in pipe where internal pressure is the primary loading [see paras. 1.4(c) and (d) for additional considerations]

1.3 Exclusions

This document does not apply to the following:

- (a) crack-like defects or mechanical surface damage not completely removed to a smooth contour by grinding
- (b) metal loss in indentations or buckles resulting in radial distortion of the pipe wall larger than 6% of the pipe outside diameter, unless a Level 3 assessment is performed in accordance with para. 2.3
- (c) grooving corrosion, selective corrosion, or preferential corrosion affecting pipe seams or girth welds
- (d) metal loss in fittings other than bends or elbows
- (e) metal loss affecting material having brittle fracture initiation characteristics [see paras. 1.7(e) and (f)] unless a Level 3 assessment is performed in accordance with para. 2.4
- (f) pipe operating at temperatures outside the range of operating temperature recognized by the governing standard or operating at temperatures in the creep range

1.4 Additional Considerations

The user is cautioned that additional considerations may apply in certain situations, described below.

(a) Pipe operating at low hoop stress levels due to internal pressure (e.g., less than 25% of SMYS) may be perforated by corrosion without inducing structural material failure. The methods and criteria provided herein do not address failure by perforation.

(b) Pipe affected by general corrosion of the pipe wall (i.e., corrosion-caused wall loss over the entire pipe surface) effectively operates at a greater hoop stress than

the nominal hoop stress based on the original wall dimension. Evaluation of individual deep pits within a generally corroded area should account for the effect of wall loss due to general corrosion.

(c) Under conditions normally encountered in buried pipelines, the hoop stress due to internal pressure is the largest stress and will govern the mode of failure. High longitudinal stresses in tension acting on metal loss having a significant circumferential extent, in unrestrained piping, could change the failure mode from longitudinal to circumferential. The methods and criteria provided herein do not address circumferential failure due to high longitudinal tensile stresses. For such situations, the user should refer to a more comprehensive fitness-for-purpose guidance document, such as API 579-1/ASME FFS-1-2007, Fitness-for-Service.

(d) Metal loss having a significant circumferential extent and acted on by high longitudinal stresses in compression could be susceptible to wrinkling or buckling. Also, the combination of hoop stress due to internal pressure and longitudinal compression could interact to lower the failure pressure in the metal loss area. The methods and criteria provided herein do not address buckling or wrinkling, or interaction of hoop stress with longitudinal compressive stresses. For such situations, the user should refer to a more comprehensive fitness-for-purpose guidance document, such as API 579-1/ASME FFS-1.

1.5 Nomenclature

A	= local area of metal loss in the longitudinal plane
A_C	= cross-sectional area of Charpy impact specimen
A_0	= local original metal area = Lt
C_V	= Charpy V-notched impact absorbed energy
D	= specified outside diameter of the pipe
d	= depth of the metal loss
E	= elastic modulus of steel
L	= length of the metal loss
L_e	= effective length = $L(\pi/4)$
M	= bulging stress magnification factor
$MAOP$	= maximum allowable operating pressure
MOP	= maximum operating pressure
P_F	= estimated failure pressure = $S_F D/2t$
P_O	= operating pressure, may equal MAOP or MOP
P_S	= safe operating pressure = P_F/SF
S_F	= estimated failure stress level
S_{flow}	= flow stress, defined in para. 1.7(b)
S_O	= hoop stress at the operating pressure, calculated as $P_O D/2t$
S_{UT}	= specified ultimate tensile strength at temperature, may equal SMTS
S_{YT}	= specified yield strength at temperature, may equal SMYS

SF = safety factor

$SMTS$ = specified minimum tensile strength at ambient conditions

$SMYS$ = specified minimum yield strength at ambient conditions

t = pipe wall thickness

$z = L^2/Dt$

$z_e = L_e^2/Dt$

1.6 Analysis Level

The user may choose to conduct a Level 0, Level 1, Level 2, or Level 3 analysis, depending on the quantity and quality of data available with which to perform an evaluation, and on the desired degree of refinement of the analysis.

(a) A Level 0 evaluation is one that relies on the tables of allowable defect length and depth found in section 3. These tables are carried over without change from earlier editions of ASME B31G and have been supplemented by the addition of tables in metric units. It is intended that a Level 0 evaluation be conducted in the field without the need for performing detailed calculations.

(b) A Level 1 evaluation is a simple calculation that relies on single measurements of the maximum depth and axial extent of metal loss. It is intended that a Level 1 evaluation be conducted in the field by an engineer, corrosion technician, coating inspector, or other individual having appropriate training. A Level 1 evaluation is also suitable for use in prioritizing metal-loss anomalies identified by inline inspection.

(c) A Level 2 evaluation is one that incorporates a greater level of detail than a Level 1 evaluation in order to produce a more accurate estimate of the failure pressure. It typically relies on detailed measurements of the corroded surface profile, accounting for the actual distribution of metal loss, and involves repetitive computations that may be facilitated by the use of computer software or spreadsheets. It is intended that a Level 2 evaluation be conducted by an engineer or technician having appropriate training. A Level 2 evaluation may be suitable for use in prioritizing metal-loss anomalies identified by high-resolution inline inspection.

(d) A Level 3 evaluation is a detailed analysis of a specific flaw in accordance with a user-defined methodology, with full justification for loadings, boundary conditions, material properties, and failure criteria. It is intended that a Level 3 evaluation be conducted by a technical specialist having appropriate expertise in the subject of fitness-for-service assessment.

1.7 Material Properties and Other Data

(a) Specified minimum material properties shall be used when conducting Level 0, Level 1, or Level 2 evaluations for the purpose of determining the need for a repair. Actual material properties from mill test reports (MTRs) or laboratory testing, if known with sufficient

confidence to warrant their usage, may be used with Level 3 evaluations. Statistical representations of material properties may be used with Levels 1, 2, or 3 for purpose of establishing a probability of failure; however, the details of such analyses are outside the scope of this document.

(b) *Flow stress* is a concept relevant to fracture mechanics and is used in the Level 1, Level 2, and Level 3 evaluations. It is not a property specified in a material grade or finished product standard. Research indicates that it may be defined variously as given below.

(1) S_{flow} for plain carbon steel operating at temperatures below 250°F (120°C) may be defined by $S_{\text{flow}} = 1.1 \times \text{SMYS}$. S_{flow} shall not exceed SMTS.

(2) S_{flow} for plain carbon and low-alloy steel having SMYS not in excess of 70 ksi (483 MPa) and operating at temperatures below 250°F (120°C) may be defined by $S_{\text{flow}} = \text{SMYS} + 10 \text{ ksi (69 MPa)}$. S_{flow} shall not exceed SMTS.

(3) S_{flow} for plain carbon and low-alloy steel having SMYS not in excess of 80 ksi (551 MPa) may be defined by $S_{\text{flow}} = (S_{YT} + S_{UT})/2$, where S_{YT} and S_{UT} are specified at the operating temperature in accordance with the ASME Boiler and Pressure Vessel Code, Section II, Part D; applicable pipe product specification; or room temperature strength multiplied by the temperature derating factor specified by the applicable construction code. Linear interpolation of strength values is allowed between listed temperatures.

(c) This document does not prescribe which definition for flow stress should be used where more than one definition applies. Where more than one definition applies, the various definitions produce acceptable though not necessarily identical results when used with any given evaluation method. It is noted that S_{flow} was defined as $1.1 \times \text{SMYS}$ in previous editions of B31G. This definition remains an inherent element of the Level 0 assessment and is recommended with the Level 1 assessment performed in accordance with para. 2.2(a).

(d) Only the specified nominal wall thickness shall be used for the uncorroded wall thickness when conducting a Level 0 evaluation. If known with confidence, the actual uncorroded wall thickness may be used with a Level 1, Level 2, or Level 3 evaluation, with a suitable adjustment of the hoop stress due to internal pressure.

(e) Pipe body material may be considered to have adequate ductile fracture initiation properties for purposes of this Standard if the material operates at a temperature no colder than 100°F (55°C) below the temperature at which 85% shear appearance is observed in a Charpy V-notched impact test.

(f) Electric resistance welded (ERW) seams that have been subjected to a normalizing heat treatment, single and double submerged arc welded seams, and girth welds made using the shielded metal arc, gas metal arc, flux cored arc, and submerged arc processes (manual or

automated, and in any combination) are considered to have adequate ductile fracture initiation properties for purposes of this Standard. Other seam and weld types shall be investigated to establish fracture properties before applying methods described herein to metal loss affecting such welds. Consideration shall be given to the disposition of workmanship flaws or manufacturing flaws within a weld or seam that could interact with metal loss due to corrosion.

(g) Some operating conditions, such as low-temperature service, or long-term exposure to sour environments or to very high temperatures, could adversely affect the ductility and fracture toughness properties of some materials. It is the user's responsibility to consider such conditions where necessary before applying methods described herein.

1.8 Evaluation Procedure

Evaluations shall be carried out in accordance with the procedures described in section 2. In addition, the following considerations apply:

(a) Units may be in any self-consistent system. It is the responsibility of the user to determine unitary conversion factors as may be required.

(b) This document makes no recommendation as to which evaluation level and evaluation method to select. All methods described herein have been demonstrated to provide reliable and conservative results when they are applied correctly and within stated limitations. Not all methods give identical numerical results or consistent degrees of conservatism. It is the pipeline operator's responsibility to select an evaluation method, based on experience and judgment, that is consistent with its operating procedures.

(c) Original source reference documents for each methodology are cited. Further references may be found in other documents available in the public domain. While each method can be applied as presented, source documents may provide additional information to the user. The user should consider referring to applicable sources as necessary in order to best implement a given method.

(d) Other evaluation methods may evolve or come into use which were not contemplated by this document. It is not the intention of this document to prohibit their use, but the user of such methods shall be able to demonstrate that the objective of a safe and reliable assessment of metal loss can be achieved.

1.9 Safety Factors and the Meaning of Acceptance

A flaw or anomaly is considered acceptable where the computed failure stress is equal to or greater than the hoop stress at the operating pressure multiplied by a suitable safety factor. There is no single safety factor that is suitable for all types of pipeline construction, for all modes of pipeline operation, or for all types of flaws or anomalies.

This document recommends a minimum safety factor equal to the ratio of the minimum hydrostatic test pressure required for the given type of pipeline construction to the MAOP or MOP, but usually not less than 1.25. Larger factors of safety may be appropriate in some cases, e.g., in locations of greater risk to the public or the environment. Lesser factors of safety may be justified in some circumstances, e.g., for limited periods of time, or where additional procedures are in place to limit modes of operation, or in a remote location having reduced consequences of failure. In establishing the safety factor for a given pipeline segment, the pipeline operator shall give consideration to the accuracy of corrosion depth and length measurements, rates of corrosion growth, the characteristics of the pipe, the reliability of surge control or excess pressure limiting methods, and the presence of external factors that affect risk.

When evaluating anomalies identified by inline inspection, use of larger factors of safety will result in smaller flaws being left in service following field investigation and pipeline repairs. This can increase the reassessment interval to the next inline inspection.

1.10 Software

The use of commercial or proprietary computer software packages, as well as purpose-written programs or spreadsheets, can greatly facilitate Level 1 evaluations, and is practically a necessity for conducting thorough Level 2 and Level 3 evaluations. It is the user's responsibility to verify the accuracy and reliability of all software and spreadsheets, and to train personnel in their correct usage.

Validation of software should include documented evidence that correct results are obtained over the full range of parameters that could reasonably be expected to occur when making evaluations. The following document summarizes the results of burst tests and service failures of line pipe affected by corrosion or artificial metal loss, and which have previously been used for the purpose of validating the evaluation methods presented herein: Kiefner, J. F., Vieth, P. H., and Roytman, I., "Continued Validation of RSTRENG," PRCI Catalog No. L51749, Contract PR 218-9304, Dec. 20, 1996.

Validation may be demonstrated by comparison of calculated results against published benchmark test data such as that found in the above reference, or against results produced by another recognized evaluation method that have been calculated in accordance with this Standard.

Validation of third-party software should also demonstrate that adequate checks or warnings are produced when parameters fall outside ranges that will ensure correct results.

1.11 Accuracy

Consideration should be given to the accuracy of recorded flaw sizes, particularly where indirect methods

are used to locate and size the flaws. Methods accounting for uncertainty in indirectly sized flaws include increasing the flaw dimension in order to account for detection tool error, or statistical analysis of the probable flaw sizes or risk of failure.

Metal-loss corrosion anomalies indicated by inline inspection may be evaluated by a Level 1 or Level 2 evaluation method. The user is cautioned against overstating the precision of evaluations applied with flaw dimensions indicated by inline inspection without adequate calibration or verification of actual flaw sizes by investigations carried out in the field.

1.12 Flaw Interaction

The methods described herein are suitable for evaluating isolated areas of metal loss. Corrosion may occur such that multiple areas of metal loss are closely spaced longitudinally or transversely. If spaced sufficiently closely, the metal loss areas may interact so as to result in failure at a lower pressure than would be expected based on an analysis of the separate flaws. The following guideline is suggested with reference to Fig. 1.12-1, based on limited testing and analysis:

(a) Flaws are considered interacting if they are spaced longitudinally or circumferentially from each other within a distance of 3 times the wall thickness ($3t$). Interacting flaws should be evaluated as a single flaw combined from all interacting flaws.

(b) Flaws are considered noninteracting if spaced outside of the above dimensions. Noninteracting flaws should be evaluated as separate flaws.

Care should be exercised when grouping or clustering anomalies indicated by inline inspection for purposes of evaluating interaction during the prioritization process. Consideration should be given to minimum thresholds of metal loss for reliable detection and sizing, minimum thresholds for reporting, and the expected mode of coating failure (e.g., localized failure versus disbondment over large areas). Methods employed for clustering of inline inspection anomalies should be validated by field verification of actual flaw dimensions and spacing.

1.13 Flaw Orientation

Corrosion caused by disbondment of continuous wrapped coatings may exhibit a helical pattern. If the helical pattern lies at an angle less than 45 deg to the pipe axis, the overall length of the corroded area indicated as L_1 in Fig. 1.13-1 shall be considered in the evaluation. If the helical pattern lies at an angle of 45 deg or greater to the pipe axis, it is sufficient to consider the most severe longitudinal section through the corroded area having a length L_2 in Fig. 1.13-1.

Corrosion may occur with a circumferential orientation, e.g., adjacent to a girth weld. It shall be evaluated for safe operating pressure as with corrosion having a helical angle greater than 45 deg to the pipe axis. Evaluation of the circumferential extent of corrosion subject

to high axial pipe stresses is outside the scope of this document. For such situations, the user should refer to a more comprehensive fitness-for-purpose guidance document, such as API 579-1/ASME FFS-1.

2 EVALUATION METHODS

2.1 Level 0 Evaluation

Tables of allowable length of corrosion are found in section 3. The tables are carried over without change from previous editions of B31G and have been supplemented by the addition of tables in metric units. They were calculated from the equations for a Level 1 evaluation in accordance with the original B31G methodology. They provide a ready reference of maximum corrosion lengths for a range of pipe sizes and depths of corrosion. The tables may be used to determine the maximum allowable longitudinal extent of a contiguous area of corrosion or an interacting cluster of metal loss areas.

Evaluations shall be carried out consistent with the procedure described in the following steps:

- Step 1.* Determine pipe diameter and nominal wall thickness from appropriate records or direct measurement of the pipe.
- Step 2.* Determine applicable pipe material properties from appropriate records.
- Step 3.* Clean the corroded pipe surface to bare metal. Care should be taken when cleaning corroded areas of a pressurized pipe.
- Step 4.* Measure the maximum depth of the corroded area, d , and longitudinal extent of the corroded area, L , as shown in Fig. 2.1-1.
- Step 5.* Locate the table corresponding to the size of the pipe, D .
- Step 6.* In the table, locate the row showing a depth equal to the measured maximum depth of the corroded area. If the exact measured value is not listed, choose the row showing the next greater depth.
- Step 7.* Read across to the column showing the wall thickness of the pipe. If the nominal wall thickness is not listed, use the column for the next thinner wall. The value, L , found at the intersection of the wall thickness column and the depth row is the maximum allowable longitudinal extent of such a corroded area.
- Step 8.* The metal loss area on the pipe is acceptable if its measured length, L , does not exceed the value of L given in the table.

The tables produce results that may be more conservative than those obtained by performing a Level 1, Level 2, or Level 3 analysis, particularly for operating hoop stress levels less than 72% of SMYS, and also for very long corroded areas. Therefore, the tables may show that a given corroded area is unsuitable for the current

operating pressure, while the use of equations given below may show that it is acceptable.

The tables were designed to provide a minimum factor of safety of 1.39 for pipelines operating with a hoop stress of 72% of SMYS. Application of the tables to the evaluation of corrosion in pipelines operating at hoop stress levels greater than 72% of SMYS will result in a factor of safety that is proportionately less.

2.2 Level 1 Evaluation

Level 1 evaluations shall be carried out consistent with the procedure described in the following steps:

- Step 1.* Determine pipe diameter and nominal wall thickness from appropriate records or direct measurement of the pipe.
- Step 2.* Clean the corroded pipe surface to bare metal. Care should be taken when cleaning corroded areas of a pressurized pipe.
- Step 3.* Measure the maximum depth of the corroded area, d , and longitudinal extent of the corroded area, L , as shown in Fig. 2.1-1.
- Step 4.* Determine applicable pipe material properties from appropriate records.
- Step 5.* Select an evaluation method and calculate the estimated failure stress, S_F .
- Step 6.* Define an acceptable safety factor, SF .
- Step 7.* Compare S_F to $SF \times S_O$.
- Step 8.* The flaw is acceptable where S_F is equal to or greater than $SF \times S_O$, or where P_F is equal to or greater than $SF \times P_O$.

If the flaw is unacceptable based on Step 8 above, the pressure can be reduced such that it is less than P_F/SF .

(a) *Original B31G*

$$M = (1 + 0.8z)^{1/2}$$

For $z \leq 20$,

$$S_F = S_{\text{flow}} \left[\frac{1 - \frac{2}{3}(d/t)}{1 - \frac{2}{3}(d/t)/M} \right]$$

For $z > 20$,

$$S_F = S_{\text{flow}}(1 - d/t)$$

Note that previous editions of B31G incorporated a definition for flow stress of $S_{\text{flow}} = 1.1 \times \text{SMYS}$. For consistency in comparison to results obtained from evaluations performed to an earlier edition, use of the same definition for flow stress is recommended.

[References: ANSI/ASME B31G-1984 and ASME B31G-1991.]

(b) *Modified B31G.* For $z \leq 50$,

$$M = (1 + 0.6275z - 0.003375z^2)^{1/2}$$

For $z > 50$,

$$M = 0.032z + 3.3$$

$$S_F = S_{\text{flow}} \left[\frac{1 - 0.85(d/t)}{1 - 0.85(d/t)/M} \right]$$

[References: (1) Kiefner, J. F., and Vieth, P. H., "Project PR3-805: A Modified Criterion for Evaluating the Remaining Strength of Corroded Pipe," AGA Catalog No. L51609, Dec. 22, 1989; (2) Kiefner, J. F., and Vieth, P. H., "New Method Corrects Criterion for Evaluating Corroded Pipe," Oil & Gas Journal, Aug. 6 and Aug. 20, 1990.]

(c) *API 579 Level 1.* The "API 579 Level 1" assessment, when reduced to its simplest form, is of a similar format to the other Level 1 methods presented herein, and therefore qualifies as a Level 1 assessment for purposes of meeting the requirements of this document.

2.3 Level 2 Evaluation

Level 2 evaluations are performed using what is known as the Effective Area Method or sometimes the RSTRENG method. Level 2 evaluations shall be carried out using a procedure similar to the ten steps described for Level 1, except that the Effective Area Method generally requires several measurements of the depth of corrosion or remaining wall thickness throughout the corroded area. The Effective Area Method is expressed as follows:

$$S_F = S_{\text{flow}} \left[\frac{1 - A/A_0}{1 - (A/A_0)/M} \right]$$

The Effective Area Method evaluates, by iteration, all possible combinations of local metal loss, A , with respect to original material, A_0 . It requires for input a detailed longitudinal distribution or profile of metal loss. The detailed profile is established by obtaining several measurements of metal loss or remaining wall thickness throughout the metal loss area. Such measurements may be arranged in a grid pattern, or may follow a "river bottom" path through the deepest areas of metal loss. Increments of measurement need not be uniform, subject to limitations of application software. If using a grid pattern, the analysis must be repeated along each meridian to establish the governing solution. For a corroded

profile defined by n measurements of depth of corrosion including the end points at nominally full wall thickness, $n!/2(n-2)!$ iterations are required to examine all possible combinations of local metal loss with respect to surrounding remaining material. The local solution resulting in the lowest calculated failure stress shall govern.

Owing to its iterative nature, it is a practical necessity to use a computer program or other algorithmic approach (e.g., a spreadsheet) in order to carry out an evaluation using the Effective Area Method.

The "API 579 Level 2" assessment, when reduced to its simplest form, is equivalent to the Effective Area Method presented herein, and therefore qualifies as a Level 2 assessment for purposes of meeting the requirements of this document. Refer to API 579-1/ASME FFS-1 for detailed instructions.

[References: Same as in para. 2.2(b).]

2.4 Level 3 Evaluation

A Level 3 evaluation typically involves a detailed analysis, such as a finite element analysis of the corroded region. The analysis should accurately consider or account for all factors which could affect the accuracy of results, including loadings including internal pressure and external forces; boundary conditions and constraints; ovality, deformations, misalignments, and discontinuities; material stress-strain characteristics; and effects of the flaw on the overall distribution of loads and stresses. A failure criterion should be developed that considers the strain capacity or fracture resistance characteristics of the material. Similar issues should be considered in developing a suitable safety factor as were described for a Level 1 or Level 2 analysis.

3 TABLES OF ALLOWABLE LENGTH OF CORROSION

The following are applicable to Tables 3-1 through 3-12M:

(a) Metal loss having a maximum depth of 10% of the nominal pipe wall thickness or less is not limited as to allowable length.

(b) Metal loss having a maximum depth exceeding 80% of the nominal pipe wall thickness shall not be evaluated using the tables of allowable length.

Fig. 1.12-1 Corrosion Pit Interaction Distances




Fig. 1.13-1 Helically Oriented Corrosion Pattern




Fig. 2.1-1 Corrosion Parameters Used in Analysis




Table 3-1 Values of L for Pipe Sizes \geq NPS 2 and $<$ NPS 6

Depth, d , in.	Wall Thickness, t , in.							
	0.083	0.109	0.125	0.141	0.154	0.172	0.188	0.218
0.01	1.99	No limit	No limit	No limit	No limit	No limit	No limit	No limit
0.02	0.92	1.94	2.44	2.59	2.71	2.86	2.30	No limit
0.03	0.53	0.85	1.13	1.51	1.94	2.86	2.99	3.22
0.04	0.39	0.60	0.75	0.93	1.11	1.40	1.74	2.74
0.05	0.31	0.47	0.58	0.70	0.82	1.00	1.18	1.62
0.06	0.25	0.39	0.48	0.58	0.66	0.79	0.92	1.21
0.07	...	0.33	0.41	0.49	0.56	0.67	0.77	0.99
0.08	...	0.28	0.35	0.43	0.49	0.58	0.67	0.84
0.09	0.31	0.38	0.43	0.51	0.59	0.74
0.10	0.27	0.33	0.39	0.46	0.53	0.66
0.11	0.30	0.35	0.41	0.48	0.60
0.12	0.31	0.38	0.43	0.55
0.13	0.34	0.40	0.50
0.14	0.37	0.46
0.15	0.34	0.43
0.16	0.40
0.17	0.37

Table 3-1M Values of L for Pipe Sizes \geq 60 mm and $<$ 168 mm O.D.

Depth, d , mm	Wall Thickness, t , mm							
	2.1	2.8	3.2	3.6	3.9	4.4	4.8	5.5
0.3	50.5	No limit	No limit	No limit	No limit	No limit	No limit	No limit
0.5	23.2	49.1	62.0	65.8	68.8	72.7	58.3	No limit
0.8	13.4	21.7	28.7	38.3	49.2	72.7	76.0	81.9
1.0	9.8	15.1	19.0	23.7	28.1	35.6	44.2	69.5
1.3	7.8	11.9	14.7	17.9	20.8	25.3	29.9	41.1
1.5	6.4	9.8	12.1	14.6	16.8	20.1	23.4	30.7
1.8	...	8.3	10.3	12.4	14.3	17.0	19.5	25.0
2.0	...	7.2	9.0	10.8	12.4	14.7	16.9	21.4
2.3	7.9	9.5	11.0	13.0	14.9	18.8
2.5	6.9	8.5	9.8	11.6	13.4	16.8
2.8	7.6	8.8	10.5	12.1	15.2
3.0	8.0	9.6	11.0	13.9
3.3	8.7	10.1	12.8
3.6	9.3	11.8
3.8	8.5	10.9
4.1	10.2
4.3	9.5

Table 3-2 Values of L for Pipe Sizes \geq NPS 6 and $<$ NPS 10

Depth, d , in.	Wall Thickness, t , in.							
	0.083	0.125	0.156	0.188	0.203	0.219	0.250	0.312
0.01	3.32	No limit	No limit	No limit	No limit	No limit	No limit	No limit
0.02	1.53	4.08	4.55	3.83	No limit	No limit	No limit	No limit
0.03	0.88	1.89	3.37	5.00	5.20	5.40	5.77	No limit
0.04	0.65	1.25	1.90	2.91	3.61	4.65	5.77	6.44
0.05	0.51	0.97	1.40	1.97	2.30	2.73	3.86	6.44
0.06	0.42	0.80	1.13	1.54	1.77	2.04	2.67	4.77
0.07	...	0.68	0.96	1.29	1.46	1.66	2.11	3.37
0.08	...	0.59	0.83	1.11	1.25	1.42	1.77	2.68
0.09	...	0.52	0.74	0.98	1.10	1.24	1.54	2.26
0.10	...	0.46	0.66	0.88	0.99	1.11	1.37	1.97
0.11	0.59	0.80	0.90	1.01	1.24	1.76
0.12	0.54	0.73	0.82	0.92	1.13	1.60
0.13	0.66	0.75	0.85	1.04	1.46
0.14	0.61	0.69	0.78	0.96	1.35
0.15	0.56	0.64	0.72	0.89	1.26
0.16	0.59	0.67	0.83	1.18
0.17	0.63	0.78	1.10
0.18	0.73	1.04
0.19	0.69	0.98
0.20	0.65	0.93
0.21	0.88
0.22	0.84
0.23	0.80
0.24	0.76

Table 3-2M Values of L for Pipe Sizes ≥ 168 mm and < 273 mm O.D.

Depth, d , mm	Wall Thickness, t , mm							
	2.1	3.2	4.0	4.8	5.2	5.6	6.4	7.9
0.3	84.4	No limit	No limit	No limit	No limit	No limit	No limit	No limit
0.5	38.8	103.6	115.7	97.4	No limit	No limit	No limit	No limit
0.8	22.4	48.0	85.6	127.0	132.0	137.1	146.4	No limit
1.0	16.4	31.8	48.1	73.8	91.6	118.1	146.4	163.6
1.3	13.0	24.6	35.5	50.0	58.5	69.3	98.0	163.6
1.5	10.7	20.3	28.7	39.1	44.9	51.7	67.8	121.1
1.8	...	17.3	24.3	32.6	37.1	42.2	53.6	85.5
2.0	...	15.0	21.1	28.2	31.9	36.0	45.0	68.1
2.3	...	13.1	18.7	24.9	28.1	31.6	39.1	57.4
2.5	...	11.6	16.7	22.3	25.1	28.3	34.8	50.2
2.8	15.0	20.2	22.8	25.6	31.4	44.8
3.0	13.6	18.4	20.8	23.4	28.7	40.6
3.3	16.9	19.1	21.5	26.4	37.2
3.6	15.5	17.6	19.8	24.4	34.4
3.8	14.3	16.3	18.4	22.7	32.0
4.1	15.1	17.1	21.2	29.9
4.3	15.9	19.8	28.0
4.6	18.6	26.4
4.8	17.5	25.0
5.1	16.4	23.6
5.3	22.4
5.6	21.3
5.8	20.2
6.1	19.2

Table 3-3 Values of L for Pipe Sizes \geq NPS 10 and $<$ NPS 16

Depth, d , in.	Wall Thickness, t , in.							
	0.156	0.219	0.250	0.307	0.344	0.365	0.438	0.500
0.02	5.80	No limit	No limit	No limit	No limit	No limit	No limit	No limit
0.03	4.29	6.87	7.34	No limit	No limit	No limit	No limit	No limit
0.04	2.41	5.92	7.34	8.14	8.62	8.87	No limit	No limit
0.05	1.78	3.48	4.91	8.14	8.62	8.87	9.72	10.39
0.06	1.44	2.59	3.40	5.77	8.62	8.87	9.72	10.39
0.07	1.22	2.11	2.69	4.13	5.53	6.62	9.72	10.39
0.08	1.06	1.81	2.26	3.30	4.22	4.85	8.37	10.39
0.09	0.94	1.59	1.96	2.80	3.48	3.93	6.10	9.38
0.10	0.84	1.42	1.74	2.45	2.99	3.35	4.92	6.95
0.11	0.75	1.28	1.57	2.19	2.65	2.94	4.18	5.64
0.12	0.68	1.17	1.44	1.98	2.39	2.64	3.67	4.81
0.13	...	1.08	1.32	1.82	2.18	2.40	3.29	4.23
0.14	...	1.00	1.22	1.68	2.01	2.21	2.99	3.80
0.15	...	0.92	1.14	1.56	1.86	2.05	2.75	3.46
0.16	...	0.86	1.06	1.46	1.74	1.91	2.55	3.19
0.17	...	0.80	0.99	1.37	1.64	1.79	2.39	2.97
0.18	0.93	1.29	1.54	1.69	2.24	2.77
0.19	0.88	1.22	1.46	1.60	2.12	2.61
0.20	0.82	1.15	1.38	1.51	2.00	2.47
0.21	1.09	1.31	1.44	1.90	2.34
0.22	1.04	1.25	1.37	1.81	2.23
0.23	0.99	1.19	1.30	1.73	2.12
0.24	0.94	1.13	1.25	1.66	2.03
0.25	1.08	1.19	1.59	1.95
0.26	1.03	1.14	1.52	1.87
0.27	0.99	1.09	1.46	1.80
0.28	1.05	1.41	1.73
0.29	1.00	1.35	1.67
0.30	1.31	1.61
0.31	1.26	1.55
0.32	1.21	1.50
0.33	1.17	1.45
0.34	1.13	1.41
0.35	1.09	1.36
0.36	1.32
0.37	1.28
0.38	1.24
0.39	1.20
0.40	1.16

Table 3-3M Values of L for Pipe Sizes ≥ 273 mm and < 406 mm O.D.

Depth, d , mm	Wall Thickness, t , mm							
	4.0	5.6	6.4	7.8	8.7	9.3	11.1	12.7
0.5	147.4	No limit	No limit	No limit	No limit	No limit	No limit	No limit
0.8	109.1	174.6	186.5	No limit	No limit	No limit	No limit	No limit
1.0	61.3	150.4	186.5	206.7	218.8	225.4	No limit	No limit
1.3	45.2	88.3	124.8	206.7	218.8	225.4	246.9	263.8
1.5	36.5	65.9	86.4	146.6	218.8	225.4	246.9	263.8
1.8	30.9	53.7	68.2	104.8	140.5	168.1	246.9	263.8
2.0	26.9	45.9	57.3	83.9	107.1	123.3	212.7	263.8
2.3	23.8	40.3	49.8	71.0	88.3	99.8	155.0	238.4
2.5	21.3	36.0	44.3	62.1	76.0	85.0	124.9	176.5
2.8	19.2	32.6	40.0	55.5	67.3	74.7	106.1	143.3
3.0	17.3	29.8	36.5	50.4	60.6	67.0	93.1	122.2
3.3	...	27.4	33.6	46.2	55.3	61.0	83.5	107.5
3.6	...	25.3	31.1	42.7	51.0	56.1	76.0	96.5
3.8	...	23.4	28.9	39.7	47.4	52.0	69.9	87.9
4.1	...	21.8	27.0	37.1	44.2	48.5	64.9	81.0
4.3	...	20.3	25.2	34.8	41.5	45.5	60.6	75.3
4.6	23.7	32.8	39.1	42.9	56.9	70.5
4.8	22.2	31.0	37.0	40.5	53.7	66.3
5.1	20.9	29.3	35.1	38.4	50.9	62.7
5.3	27.8	33.3	36.5	48.4	59.4
5.6	26.4	31.7	34.8	46.1	56.6
5.8	25.1	30.2	33.1	44.0	54.0
6.1	23.8	28.8	31.7	42.1	51.6
6.4	27.5	30.3	40.3	49.5
6.6	26.3	29.0	38.7	47.5
6.9	25.1	27.7	37.2	45.7
7.1	26.6	35.7	44.0
7.4	25.5	34.4	42.4
7.6	33.2	40.9
7.9	32.0	39.5
8.1	30.8	38.1
8.4	29.7	36.9
8.6	28.7	35.7
8.9	27.7	34.6
9.1	33.5
9.4	32.4
9.7	31.4
9.9	30.5
10.2	29.6

Table 3-4 Values of L for Pipe Sizes \geq NPS 16 and $<$ NPS 20

Depth, d , in.	Wall Thickness, t , in.							
	0.188	0.250	0.312	0.344	0.375	0.438	0.500	0.625
0.02	5.96	No limit	No limit	No limit	No limit	No limit	No limit	No limit
0.03	7.77	8.96	No limit	No limit	No limit	No limit	No limit	No limit
0.04	4.52	8.96	10.01	10.51	10.97	No limit	No limit	No limit
0.05	3.06	6.00	10.01	10.51	10.97	11.86	12.67	No limit
0.06	2.39	4.15	7.41	10.51	10.97	11.86	12.67	No limit
0.07	2.00	3.28	5.23	6.75	8.84	11.86	12.67	14.17
0.08	1.73	2.75	4.17	5.14	6.34	10.21	12.67	14.17
0.09	1.52	2.39	3.51	4.24	5.08	7.44	11.45	14.17
0.10	1.37	2.13	3.07	3.65	4.30	6.00	8.48	14.17
0.11	1.24	1.92	2.74	3.23	3.77	5.10	6.88	13.85
0.12	1.13	1.75	2.48	2.91	3.37	4.47	5.87	10.53
0.13	1.03	1.61	2.27	2.66	3.06	4.01	5.16	8.65
0.14	0.95	1.49	2.10	2.45	2.81	3.65	4.63	7.43
0.15	0.87	1.39	1.96	2.28	2.61	3.36	4.22	6.56
0.16	...	1.30	1.83	2.13	2.43	3.12	3.89	5.91
0.17	...	1.21	1.72	1.99	2.28	2.91	3.62	5.40
0.18	...	1.14	1.62	1.88	2.15	2.74	3.38	4.99
0.19	...	1.07	1.53	1.78	2.03	2.58	3.18	4.64
0.20	...	1.00	1.44	1.68	1.92	2.45	3.01	4.35
0.21	1.37	1.60	1.83	2.32	2.85	4.10
0.22	1.30	1.52	1.74	2.21	2.72	3.88
0.23	1.24	1.45	1.66	2.11	2.59	3.69
0.24	1.18	1.38	1.59	2.02	2.48	3.52
0.25	1.32	1.52	1.94	2.38	3.36
0.26	1.26	1.45	1.86	2.28	3.22
0.27	1.21	1.39	1.79	2.19	3.10
0.28	1.34	1.72	2.11	2.98
0.29	1.28	1.65	2.03	2.87
0.30	1.23	1.59	1.96	2.77
0.31	1.53	1.90	2.68
0.32	1.48	1.83	2.59
0.33	1.43	1.77	2.51
0.34	1.38	1.71	2.43
0.35	1.33	1.66	2.36
0.36	1.61	2.29
0.37	1.56	2.23
0.38	1.51	2.16
0.39	1.46	2.11
0.40	1.42	2.05
0.41	1.99
0.42	1.94
0.43	1.89
0.44	1.84
0.45	1.80
0.46	1.75
0.47	1.71
0.48	1.67
0.49	1.63
0.50	1.59

Table 3-4M Values of L for Pipe Sizes ≥ 406 mm and < 508 mm O.D.

Depth, d , mm	Wall Thickness, t , mm							
	4.8	6.4	7.9	8.7	9.5	11.1	12.7	15.9
0.5	151.3	No limit	No limit	No limit	No limit	No limit	No limit	No limit
0.8	197.4	227.6	No limit	No limit	No limit	No limit	No limit	No limit
1.0	114.8	227.6	254.2	267.0	278.7	No limit	No limit	No limit
1.3	77.7	152.3	254.2	267.0	278.7	301.2	321.9	No limit
1.5	60.8	105.4	188.2	267.0	278.7	301.2	321.9	No limit
1.8	50.7	83.2	132.9	171.4	224.5	301.2	321.9	359.8
2.0	43.8	69.9	105.8	130.6	161.2	259.5	321.9	359.8
2.3	38.7	60.8	89.3	107.7	129.1	189.1	290.8	359.8
2.5	34.7	54.1	77.9	92.8	109.3	152.4	215.4	359.8
2.8	31.4	48.8	69.6	82.1	95.7	129.5	174.8	351.8
3.0	28.6	44.5	63.0	73.9	85.6	113.6	149.1	267.5
3.3	26.2	41.0	57.8	67.5	77.8	101.8	131.1	219.8
3.6	24.1	37.9	53.4	62.2	71.4	92.7	117.7	188.7
3.8	22.2	35.3	49.7	57.8	66.2	85.3	107.3	166.7
4.1	...	32.9	46.4	54.0	61.7	79.1	98.9	150.1
4.3	...	30.8	43.6	50.7	57.9	73.9	91.9	137.1
4.6	...	28.9	41.1	47.7	54.5	69.5	86.0	126.6
4.8	...	27.1	38.8	45.1	51.5	65.6	80.9	117.9
5.1	...	25.5	36.7	42.8	48.9	62.1	76.4	110.5
5.3	34.8	40.6	46.4	59.0	72.5	104.2
5.6	33.0	38.6	44.2	56.2	69.0	98.6
5.8	31.4	36.8	42.2	53.7	65.8	93.7
6.1	29.9	35.1	40.3	51.3	63.0	89.4
6.4	33.5	38.6	49.2	60.3	85.5
6.6	32.0	36.9	47.2	57.9	81.9
6.9	30.6	35.4	45.4	55.7	78.7
7.1	33.9	43.6	53.6	75.7
7.4	32.5	42.0	51.7	72.9
7.6	31.2	40.4	49.9	70.4
7.9	39.0	48.2	68.0
8.1	37.6	46.5	65.8
8.4	36.3	45.0	63.7
8.6	35.0	43.6	61.8
8.9	33.8	42.2	60.0
9.1	40.9	58.2
9.4	39.6	56.6
9.7	38.4	55.0
9.9	37.2	53.5
10.2	36.1	52.0
10.4	50.7
10.7	49.3
10.9	48.1
11.2	46.9
11.4	45.7
11.7	44.5
11.9	43.4
12.2	42.4
12.4	41.3
12.7	40.3

Table 3-5 Values of L for Pipe Sizes \geq NPS 20 and $<$ NPS 24

Depth, d , in.	Wall Thickness, t , in.							
	0.219	0.250	0.344	0.406	0.469	0.500	0.562	0.625
0.03	9.38	10.02	No limit	No limit	No limit	No limit	No limit	No limit
0.04	8.08	10.02	11.75	No limit	No limit	No limit	No limit	No limit
0.05	4.74	6.70	11.75	12.77	13.72	14.17	No limit	No limit
0.06	3.54	4.64	11.75	12.77	13.72	14.17	15.02	No limit
0.07	2.88	3.66	7.54	12.77	13.72	14.17	15.02	15.84
0.08	2.46	3.08	5.75	8.86	13.72	14.17	15.02	15.84
0.09	2.16	2.68	4.74	6.83	10.21	12.80	15.02	15.84
0.10	1.93	2.38	4.08	5.66	7.94	9.48	14.12	15.84
0.11	1.75	2.15	3.61	4.89	6.61	7.69	10.61	15.49
0.12	1.60	1.96	3.26	4.34	5.73	6.56	8.67	11.77
0.13	1.47	1.80	2.97	3.92	5.09	5.77	7.42	9.67
0.14	1.36	1.67	2.74	3.58	4.60	5.18	6.54	8.31
0.15	1.26	1.55	2.54	3.31	4.22	4.72	5.88	7.34
0.16	1.17	1.45	2.38	3.08	3.90	4.35	5.37	6.61
0.17	1.09	1.36	2.23	2.89	3.64	4.04	4.95	6.04
0.18	...	1.27	2.10	2.72	3.41	3.78	4.61	5.57
0.19	...	1.19	1.99	2.56	3.21	3.56	4.32	5.19
0.20	...	1.12	1.88	2.43	3.04	3.36	4.07	4.87
0.21	1.79	2.31	2.89	3.19	3.85	4.59
0.22	1.70	2.20	2.75	3.04	3.65	4.34
0.23	1.62	2.10	2.63	2.90	3.48	4.13
0.24	1.55	2.01	2.51	2.77	3.32	3.93
0.25	1.48	1.92	2.41	2.66	3.18	3.76
0.26	1.41	1.84	2.31	2.55	3.05	3.61
0.27	1.35	1.77	2.22	2.45	2.94	3.46
0.28	1.70	2.14	2.36	2.83	3.33
0.29	1.64	2.06	2.27	2.73	3.21
0.30	1.57	1.99	2.19	2.63	3.10
0.31	1.51	1.92	2.12	2.54	2.99
0.32	1.46	1.85	2.05	2.46	2.90
0.33	1.79	1.98	2.38	2.81
0.34	1.73	1.92	2.31	2.72
0.35	1.67	1.86	2.24	2.64
0.36	1.62	1.80	2.17	2.56
0.37	1.56	1.74	2.11	2.49
0.38	1.69	2.05	2.42
0.39	1.64	1.99	2.35
0.40	1.59	1.93	2.29
0.41	1.88	2.23
0.42	1.83	2.17
0.43	1.78	2.12
0.44	1.73	2.06
0.45	2.01
0.46	1.96
0.47	1.91
0.48	1.86
0.49	1.82
0.50	1.78

Table 3-5M Values of L for Pipe Sizes ≥ 508 mm and < 610 mm O.D.

Depth, d , mm	Wall Thickness, t , mm							
	5.6	6.4	8.7	10.3	11.9	12.7	14.3	15.9
0.8	238.1	254.4	No limit	No limit	No limit	No limit	No limit	No limit
1.0	205.1	254.4	298.5	No limit	No limit	No limit	No limit	No limit
1.3	120.5	170.3	298.5	324.3	348.5	359.8	No limit	No limit
1.5	89.8	117.8	298.5	324.3	348.5	359.8	381.5	No limit
1.8	73.3	93.1	191.6	324.3	348.5	359.8	381.5	402.3
2.0	62.6	78.2	146.0	225.2	348.5	359.8	381.5	402.3
2.3	54.9	68.0	120.4	173.5	259.5	325.1	381.5	402.3
2.5	49.1	60.4	103.7	143.8	201.7	240.8	358.6	402.3
2.8	44.4	54.6	91.8	124.3	168.0	195.4	269.5	393.4
3.0	40.6	49.8	82.7	110.2	145.5	166.7	220.2	299.1
3.3	37.3	45.8	75.5	99.5	129.3	146.6	188.5	245.7
3.6	34.5	42.4	69.6	91.0	116.9	131.6	166.1	211.0
3.8	32.0	39.4	64.6	84.1	107.1	119.9	149.4	186.3
4.1	29.7	36.8	60.4	78.3	99.1	110.5	136.4	167.8
4.3	27.7	34.4	56.6	73.3	92.4	102.7	125.8	153.3
4.6	...	32.3	53.4	69.0	86.6	96.1	117.1	141.6
4.8	...	30.3	50.5	65.1	81.6	90.4	109.6	131.8
5.1	...	28.5	47.8	61.7	77.2	85.5	103.3	123.6
5.3	45.4	58.7	73.3	81.1	97.7	116.5
5.6	43.2	55.9	69.8	77.1	92.8	110.3
5.8	41.2	53.4	66.7	73.6	88.4	104.8
6.1	39.3	51.0	63.8	70.4	84.4	99.9
6.4	37.5	48.9	61.1	67.5	80.9	95.5
6.6	35.8	46.9	58.7	64.8	77.6	91.6
6.9	34.2	45.0	56.4	62.3	74.6	88.0
7.1	43.2	54.3	60.0	71.8	84.6
7.4	41.5	52.3	57.8	69.2	81.6
7.6	39.9	50.4	55.8	66.8	78.7
7.9	38.4	48.7	53.8	64.6	76.1
8.1	37.0	47.0	52.0	62.5	73.6
8.4	45.4	50.3	60.5	71.3
8.6	43.9	48.7	58.6	69.1
8.9	42.4	47.2	56.8	67.0
9.1	41.1	45.7	55.1	65.1
9.4	39.7	44.3	53.5	63.2
9.7	42.9	52.0	61.5
9.9	41.6	50.5	59.8
10.2	40.3	49.1	58.2
10.4	47.7	56.6
10.7	46.4	55.2
10.9	45.1	53.7
11.2	43.9	52.4
11.4	51.1
11.7	49.8
11.9	48.6
12.2	47.4
12.4	46.2
12.7	45.1

Table 3-6 Values of L for Pipe Sizes \geq NPS 24 and $<$ NPS 30

Depth, d , in.	Wall Thickness, t , in.							
	0.250	0.312	0.375	0.438	0.469	0.500	0.562	0.625
0.03	10.97	No limit	No limit	No limit	No limit	No limit	No limit	No limit
0.04	10.97	12.26	13.44	No limit	No limit	No limit	No limit	No limit
0.05	7.34	12.26	13.44	14.53	15.03	15.52	No limit	No limit
0.06	5.08	9.07	13.44	14.53	15.03	15.52	16.45	No limit
0.07	4.01	6.41	10.83	14.53	15.03	15.52	16.45	17.35
0.08	3.37	5.10	7.77	12.51	15.03	15.52	16.45	17.35
0.09	2.93	4.30	6.22	9.12	11.19	14.02	16.45	17.35
0.10	2.61	3.76	5.27	7.35	8.70	10.38	15.47	17.35
0.11	2.35	3.35	4.61	6.24	7.24	8.43	11.62	16.96
0.12	2.15	3.04	4.13	5.48	6.28	7.19	9.50	12.90
0.13	1.98	2.79	3.75	4.91	5.58	6.32	8.13	10.60
0.14	1.83	2.57	3.45	4.47	5.04	5.68	7.17	9.10
0.15	1.70	2.39	3.19	4.11	4.62	5.17	6.44	8.04
0.16	1.59	2.24	2.98	3.82	4.27	4.77	5.88	7.24
0.17	1.49	2.10	2.79	3.57	3.98	4.43	5.43	6.61
0.18	1.39	1.98	2.63	3.35	3.74	4.15	5.05	6.11
0.19	1.31	1.87	2.49	3.16	3.52	3.90	4.73	5.69
0.20	1.23	1.77	2.36	2.99	3.33	3.69	4.45	5.33
0.21	...	1.68	2.24	2.85	3.16	3.50	4.21	5.02
0.22	...	1.59	2.13	2.71	3.01	3.33	4.00	4.76
0.23	...	1.51	2.03	2.59	2.88	3.17	3.81	4.52
0.24	...	1.44	1.94	2.48	2.75	3.04	3.64	4.31
0.25	1.86	2.37	2.64	2.91	3.49	4.12
0.26	1.78	2.28	2.53	2.79	3.35	3.95
0.27	1.71	2.19	2.43	2.69	3.22	3.79
0.28	1.64	2.10	2.34	2.59	3.10	3.65
0.29	1.57	2.02	2.26	2.49	2.99	3.52
0.30	1.51	1.95	2.17	2.40	2.88	3.39
0.31	1.88	2.10	2.32	2.78	3.28
0.32	1.81	2.03	2.24	2.69	3.17
0.33	1.75	1.96	2.17	2.61	3.07
0.34	1.69	1.89	2.10	2.53	2.98
0.35	1.63	1.83	2.03	2.45	2.89
0.36	1.77	1.97	2.38	2.81
0.37	1.71	1.91	2.31	2.73
0.38	1.85	2.24	2.65
0.39	1.79	2.18	2.58
0.40	1.74	2.12	2.51
0.41	2.06	2.44
0.42	2.00	2.38
0.43	1.95	2.32
0.44	1.89	2.26
0.45	2.20
0.46	2.15
0.47	2.09
0.48	2.04
0.49	1.99
0.50	1.94

Table 3-6M Values of L for Pipe Sizes ≥ 610 mm and < 762 mm O.D.

Depth, d , mm	Wall Thickness, t , mm							
	6.4	7.9	9.5	11.1	11.9	12.7	14.3	15.9
0.8	278.7	No limit	No limit	No limit	No limit	No limit	No limit	No limit
1.0	278.7	311.4	341.4	No limit	No limit	No limit	No limit	No limit
1.3	186.5	311.4	341.4	368.9	381.8	394.2	No limit	No limit
1.5	129.1	230.5	341.4	368.9	381.8	394.2	417.9	No limit
1.8	102.0	162.8	275.0	368.9	381.8	394.2	417.9	440.7
2.0	85.6	129.6	197.4	317.8	381.8	394.2	417.9	440.7
2.3	74.5	109.3	158.1	231.6	284.2	356.2	417.9	440.7
2.5	66.2	95.5	133.9	186.7	221.0	263.8	392.9	440.7
2.8	59.8	85.2	117.2	158.6	184.0	214.1	295.2	430.9
3.0	54.5	77.2	104.9	139.1	159.4	182.6	241.2	327.6
3.3	50.2	70.8	95.3	124.7	141.6	160.6	206.5	269.1
3.6	46.4	65.4	87.5	113.5	128.1	144.2	182.0	231.1
3.8	43.2	60.8	81.1	104.4	117.3	131.4	163.7	204.1
4.1	40.3	56.9	75.6	96.9	108.5	121.1	149.4	183.8
4.3	37.7	53.4	70.9	90.6	101.2	112.5	137.8	167.9
4.6	35.4	50.3	66.8	85.1	94.9	105.3	128.2	155.1
4.8	33.2	47.5	63.1	80.3	89.4	99.1	120.1	144.4
5.1	31.2	44.9	59.8	76.1	84.6	93.6	113.1	135.4
5.3	...	42.6	56.9	72.3	80.4	88.8	107.0	127.6
5.6	...	40.5	54.2	68.8	76.5	84.5	101.6	120.8
5.8	...	38.5	51.7	65.7	73.0	80.6	96.8	114.8
6.1	...	36.6	49.4	62.9	69.9	77.1	92.5	109.5
6.4	47.2	60.3	67.0	73.9	88.6	104.7
6.6	45.2	57.8	64.3	71.0	85.0	100.3
6.9	43.3	55.5	61.8	68.2	81.7	96.3
7.1	41.5	53.4	59.5	65.7	78.7	92.7
7.4	39.9	51.4	57.3	63.3	75.8	89.3
7.6	38.3	49.5	55.2	61.1	73.2	86.2
7.9	47.7	53.3	59.0	70.7	83.3
8.1	46.1	51.5	57.0	68.4	80.6
8.4	44.4	49.7	55.1	66.2	78.1
8.6	42.9	48.1	53.3	64.2	75.7
8.9	41.4	46.5	51.7	62.2	73.4
9.1	45.0	50.0	60.4	71.3
9.4	43.5	48.5	58.6	69.3
9.7	47.0	56.9	67.3
9.9	45.6	55.3	65.5
10.2	44.2	53.7	63.7
10.4	52.2	62.0
10.7	50.8	60.4
10.9	49.4	58.9
11.2	48.1	57.4
11.4	55.9
11.7	54.5
11.9	53.2
12.2	51.9
12.4	50.6
12.7	49.4

Table 3-7 Values of L for Pipe Sizes \geq NPS 30 and $<$ NPS 36

Depth, d , in.	Wall Thickness, t , in.						
	0.250	0.312	0.375	0.438	0.500	0.625	0.688
0.03	12.27	No limit	No limit	No limit	No limit	No limit	No limit
0.04	12.27	13.71	15.03	No limit	No limit	No limit	No limit
0.05	8.21	13.71	15.03	16.24	17.35	No limit	No limit
0.06	5.68	10.14	15.03	16.24	17.35	No limit	No limit
0.07	4.49	7.17	12.10	16.24	17.35	19.40	20.35
0.08	3.77	5.70	8.69	13.99	17.35	19.40	20.35
0.09	3.28	4.81	6.96	10.19	15.68	19.40	20.35
0.10	2.91	4.20	5.89	8.22	11.61	19.40	20.35
0.11	2.63	3.75	5.16	6.98	9.42	18.97	20.35
0.12	2.40	3.40	4.62	6.12	8.04	14.42	20.35
0.13	2.21	3.11	4.19	5.49	7.07	11.85	15.82
0.14	2.04	2.88	3.85	5.00	6.35	10.17	13.07
0.15	1.90	2.68	3.57	4.60	5.78	8.98	11.25
0.16	1.77	2.50	3.33	4.27	5.33	8.09	9.96
0.17	1.66	2.35	3.12	3.99	4.95	7.39	8.98
0.18	1.56	2.21	2.94	3.75	4.63	6.83	8.21
0.19	1.46	2.09	2.78	3.53	4.36	6.36	7.59
0.20	1.38	1.98	2.63	3.35	4.12	5.96	7.07
0.21	...	1.88	2.50	3.18	3.91	5.62	6.63
0.22	...	1.78	2.38	3.03	3.72	5.32	6.26
0.23	...	1.69	2.27	2.89	3.55	5.05	5.93
0.24	...	1.61	2.17	2.77	3.39	4.82	5.64
0.25	2.08	2.65	3.25	4.61	5.38
0.26	1.99	2.54	3.12	4.42	5.15
0.27	1.91	2.44	3.00	4.24	4.94
0.28	1.83	2.35	2.89	4.08	4.74
0.29	1.75	2.26	2.79	3.93	4.57
0.30	1.68	2.18	2.69	3.80	4.41
0.31	2.10	2.60	3.67	4.26
0.32	2.03	2.51	3.55	4.12
0.33	1.96	2.43	3.44	3.99
0.34	1.89	2.35	3.33	3.86
0.35	1.82	2.27	3.23	3.75
0.36	2.20	3.14	3.64
0.37	2.13	3.05	3.54
0.38	2.07	2.96	3.44
0.39	2.01	2.88	3.35
0.40	1.94	2.81	3.26
0.41	2.73	3.18
0.42	2.66	3.10
0.43	2.59	3.02
0.44	2.53	2.95
0.45	2.46	2.87
0.46	2.40	2.81
0.47	2.34	2.74
0.48	2.28	2.68
0.49	2.23	2.62
0.50	2.17	2.56
0.51	2.50
0.52	2.44
0.53	2.39
0.54	2.33
0.55	2.28

Table 3-7M Values of L for Pipe Sizes ≥ 762 mm and < 914 mm O.D.

Depth, d , mm	Wall Thickness, t , mm						
	6.4	7.9	9.5	11.1	12.7	15.9	17.5
0.8	311.6	No limit	No limit	No limit	No limit	No limit	No limit
1.0	311.6	348.1	381.7	No limit	No limit	No limit	No limit
1.3	208.5	348.1	381.7	412.5	440.7	No limit	No limit
1.5	144.3	257.7	381.7	412.5	440.7	No limit	No limit
1.8	114.0	182.0	307.4	412.5	440.7	492.7	517.0
2.0	95.7	144.9	220.7	355.3	440.7	492.7	517.0
2.3	83.2	122.2	176.8	258.9	398.2	492.7	517.0
2.5	74.0	106.7	149.7	208.7	294.9	492.7	517.0
2.8	66.8	95.3	131.0	177.3	239.3	481.8	517.0
3.0	61.0	86.3	117.2	155.6	204.1	366.3	517.0
3.3	56.1	79.1	106.5	139.4	179.5	300.9	401.9
3.6	51.9	73.1	97.8	126.9	161.2	258.4	331.9
3.8	48.3	68.0	90.6	116.8	146.9	228.2	285.8
4.1	45.1	63.6	84.6	108.4	135.4	205.5	252.9
4.3	42.2	59.7	79.3	101.3	125.8	187.8	228.1
4.6	39.6	56.2	74.7	95.1	117.7	173.4	208.6
4.8	37.1	53.1	70.6	89.8	110.8	161.5	192.8
5.1	34.9	50.3	66.9	85.0	104.7	151.3	179.6
5.3	...	47.7	63.6	80.8	99.3	142.7	168.5
5.6	...	45.2	60.6	77.0	94.5	135.1	158.9
5.8	...	43.0	57.8	73.5	90.2	128.4	150.6
6.1	...	40.9	55.2	70.3	86.2	122.4	143.2
6.4	52.8	67.4	82.6	117.0	136.6
6.6	50.6	64.6	79.3	112.2	130.7
6.9	48.4	62.1	76.3	107.7	125.4
7.1	46.5	59.7	73.4	103.6	120.5
7.4	44.6	57.5	70.8	99.9	116.0
7.6	42.8	55.4	68.3	96.4	111.9
7.9	53.4	65.9	93.2	108.1
8.1	51.5	63.7	90.1	104.5
8.4	49.7	61.6	87.3	101.2
8.6	48.0	59.6	84.6	98.1
8.9	46.3	57.7	82.1	95.2
9.1	55.9	79.7	92.5
9.4	54.2	77.4	89.8
9.7	52.5	75.3	87.4
9.9	50.9	73.2	85.0
10.2	49.4	71.3	82.8
10.4	69.4	80.7
10.7	67.6	78.6
10.9	65.8	76.7
11.2	64.2	74.8
11.4	62.5	73.0
11.7	61.0	71.3
11.9	59.5	69.6
12.2	58.0	68.0
12.4	56.6	66.4
12.7	55.2	64.9
13.0	63.5
13.2	62.0
13.5	60.6
13.7	59.3
14.0	58.0

Table 3-8 Values of L for Pipe Sizes \geq NPS 36 and $<$ NPS 42

Depth, d , in.	Wall Thickness, t , in.							
	0.250	0.281	0.312	0.375	0.406	0.469	0.562	0.688
0.03	13.44	11.12	No limit	No limit	No limit	No limit	No limit	No limit
0.04	13.44	14.25	15.01	16.46	No limit	No limit	No limit	No limit
0.05	8.99	13.40	15.01	16.46	17.13	18.41	No limit	No limit
0.06	6.22	8.22	11.11	16.46	17.13	18.41	20.15	No limit
0.07	4.92	6.21	7.85	13.26	17.13	18.41	20.15	22.30
0.08	4.13	5.09	6.25	9.52	11.89	18.41	20.15	22.30
0.09	3.59	4.37	5.27	7.62	9.16	13.70	20.15	22.30
0.10	3.19	3.86	4.60	6.46	7.60	10.66	18.94	22.30
0.11	2.88	3.47	4.11	5.65	6.56	8.87	14.23	22.30
0.12	2.63	3.15	3.72	5.06	5.82	7.69	11.63	22.30
0.13	2.42	2.90	3.41	4.59	5.26	6.83	9.95	17.33
0.14	2.24	2.68	3.15	4.22	4.81	6.18	8.78	14.31
0.15	2.08	2.50	2.93	3.91	4.44	5.66	7.89	12.33
0.16	1.94	2.33	2.74	3.65	4.13	5.23	7.20	10.91
0.17	1.82	2.19	2.57	3.42	3.87	4.88	6.65	9.84
0.18	1.71	2.06	2.42	3.22	3.64	4.58	6.18	9.00
0.19	1.60	1.94	2.29	3.04	3.44	4.31	5.79	8.31
0.20	1.51	1.83	2.17	2.89	3.26	4.08	5.45	7.75
0.21	...	1.73	2.06	2.74	3.10	3.87	5.16	7.27
0.22	...	1.64	1.95	2.61	2.95	3.69	4.90	6.85
0.23	1.85	2.49	2.82	3.52	4.67	6.49
0.24	1.76	2.38	2.70	3.37	4.46	6.18
0.25	2.28	2.58	3.23	4.27	5.89
0.26	2.18	2.48	3.10	4.10	5.64
0.27	2.09	2.38	2.98	3.94	5.41
0.28	2.00	2.28	2.87	3.79	5.20
0.29	1.92	2.19	2.76	3.66	5.00
0.30	1.84	2.11	2.66	3.53	4.83
0.31	2.03	2.57	3.41	4.66
0.32	1.95	2.48	3.30	4.51
0.33	2.40	3.19	4.37
0.34	2.32	3.09	4.23
0.35	2.24	3.00	4.11
0.36	2.17	2.91	3.99
0.37	2.10	2.83	3.87
0.38	2.74	3.77
0.39	2.67	3.67
0.40	2.59	3.57
0.41	2.52	3.48
0.42	2.45	3.39
0.43	2.38	3.31
0.44	2.32	3.23
0.45	3.15
0.46	3.07
0.47	3.00
0.48	2.93
0.49	2.87
0.50	2.80
0.51	2.74
0.52	2.68
0.53	2.62
0.54	2.56
0.55	2.50

Table 3-8M Values of L for Pipe Sizes ≥ 914 mm and $< 1\ 066$ mm O.D.

Depth, d , mm	Wall Thickness, t , mm							
	6.4	7.1	7.9	9.5	10.3	11.9	14.3	17.5
0.8	341.4	282.5	No limit	No limit	No limit	No limit	No limit	No limit
1.0	341.4	361.9	381.4	418.1	No limit	No limit	No limit	No limit
1.3	228.4	340.2	381.4	418.1	435.0	467.6	No limit	No limit
1.5	158.1	208.9	282.3	418.1	435.0	467.6	511.8	No limit
1.8	124.9	157.6	199.4	336.8	435.0	467.6	511.8	566.3
2.0	104.9	129.4	158.7	241.7	302.1	467.6	511.8	566.3
2.3	91.2	111.0	133.9	193.6	232.8	348.1	511.8	566.3
2.5	81.1	98.0	116.9	164.0	193.0	270.6	481.2	566.3
2.8	73.2	88.0	104.3	143.5	166.7	225.4	361.6	566.3
3.0	66.8	80.1	94.6	128.4	147.9	195.2	295.4	566.3
3.3	61.4	73.6	86.7	116.7	133.5	173.5	252.9	440.2
3.6	56.9	68.1	80.1	107.2	122.1	156.9	222.9	363.6
3.8	52.9	63.4	74.5	99.3	112.8	143.7	200.5	313.1
4.1	49.4	59.3	69.6	92.6	105.0	132.9	183.0	277.1
4.3	46.2	55.6	65.4	86.9	98.3	123.9	168.8	249.9
4.6	43.3	52.3	61.6	81.8	92.5	116.2	157.0	228.5
4.8	40.7	49.3	58.2	77.3	87.4	109.5	147.1	211.2
5.1	38.3	46.5	55.1	73.3	82.8	103.6	138.5	196.8
5.3	...	44.0	52.2	69.7	78.7	98.4	131.1	184.6
5.6	...	41.6	49.6	66.3	75.0	93.7	124.5	174.1
5.8	47.1	63.3	71.6	89.5	118.6	164.9
6.1	44.8	60.5	68.5	85.6	113.3	156.9
6.4	57.8	65.6	82.0	108.5	149.7
6.6	55.4	62.9	78.7	104.1	143.2
6.9	53.1	60.3	75.7	100.1	137.3
7.1	50.9	58.0	72.8	96.3	132.0
7.4	48.8	55.7	70.2	92.9	127.1
7.6	46.9	53.6	67.7	89.6	122.6
7.9	51.6	65.3	86.6	118.4
8.1	49.7	63.0	83.8	114.5
8.4	60.9	81.1	110.9
8.6	58.9	78.6	107.5
8.9	56.9	76.2	104.3
9.1	55.1	73.9	101.3
9.4	53.3	71.8	98.4
9.7	69.7	95.7
9.9	67.7	93.2
10.2	65.8	90.7
10.4	64.0	88.4
10.7	62.2	86.1
10.9	60.5	84.0
11.2	58.9	82.0
11.4	80.0
11.7	78.1
11.9	76.3
12.2	74.5
12.4	72.8
12.7	71.1
13.0	69.5
13.2	68.0
13.5	66.4
13.7	65.0
14.0	63.5

Table 3-9 Values of L for Pipe Sizes \geq NPS 42 and $<$ NPS 48

Depth, <i>d</i> , in.	Wall Thickness, <i>t</i> , in.																
	0.344	0.406	0.438	0.469	0.500	0.562	0.625	0.688	0.750	0.812	0.875	0.938	1.000	1.062	1.125	1.188	1.250
0.03	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
0.04	17.03	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
0.05	17.03	18.50	19.21	19.88	20.53	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
0.06	17.03	18.50	19.21	19.88	20.53	21.77	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
0.07	10.93	18.50	19.21	19.88	20.53	21.77	22.95	24.08	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
0.08	8.33	12.85	16.55	19.88	20.53	21.77	22.95	24.08	25.14	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
0.09	6.87	9.90	12.06	14.80	18.55	21.77	22.95	24.08	25.14	26.16	27.16	No limit	No limit	No limit	No limit	No limit	No limit
0.10	5.92	8.21	9.72	11.51	13.74	20.46	22.95	24.08	25.14	26.16	27.16	28.12	29.03	No limit	No limit	No limit	No limit
0.11	5.24	7.09	8.26	9.58	11.15	15.37	22.44	24.08	25.14	26.16	27.16	28.12	29.03	29.92	No limit	No limit	No limit
0.12	4.72	6.29	7.25	8.30	9.51	12.56	17.06	24.08	25.14	26.16	27.16	28.12	29.03	29.92	30.79	31.65	No limit
0.13	4.31	5.68	6.50	7.38	8.36	10.75	14.02	18.72	25.14	26.16	27.16	28.12	29.03	29.92	30.79	31.65	32.46
0.14	3.97	5.19	5.91	6.67	7.51	9.48	12.04	15.46	20.25	26.16	27.16	28.12	29.03	29.92	30.79	31.65	32.46
0.15	3.69	4.80	5.44	6.11	6.84	8.53	10.63	13.32	16.82	21.75	27.16	28.12	29.03	29.92	30.79	31.65	32.46
0.16	3.44	4.47	5.05	5.65	6.31	7.78	9.57	11.78	14.54	18.17	23.31	28.12	29.03	29.92	30.79	31.65	32.46
0.17	3.23	4.18	4.72	5.27	5.86	7.18	8.75	10.63	12.89	15.75	19.56	24.84	29.03	29.92	30.79	31.65	32.46
0.18	3.05	3.93	4.43	4.94	5.48	6.68	8.08	9.72	11.65	14.00	17.00	20.93	26.23	29.92	30.79	31.65	32.46
0.19	2.88	3.72	4.18	4.66	5.16	6.26	7.52	8.98	10.66	12.66	15.14	18.25	22.22	27.60	30.79	31.65	32.46
0.20	2.73	3.52	3.96	4.41	4.88	5.89	7.05	8.37	9.86	11.60	13.71	16.28	19.43	23.48	29.04	31.65	32.46
0.21	2.59	3.35	3.76	4.18	4.63	5.57	6.65	7.85	9.20	10.74	12.58	14.76	17.36	20.59	24.80	30.45	32.46
0.22	2.46	3.19	3.59	3.99	4.40	5.29	6.29	7.40	8.63	10.03	11.65	13.55	15.77	18.44	21.80	26.11	31.74
0.23	2.35	3.05	3.42	3.80	4.20	5.04	5.98	7.01	8.15	9.42	10.88	12.56	14.49	16.77	19.56	23.00	27.32
0.24	2.24	2.91	3.27	3.64	4.02	4.82	5.70	6.67	7.72	8.89	10.23	11.74	13.45	15.43	17.81	20.67	24.13
0.25	2.14	2.79	3.14	3.49	3.85	4.61	5.45	6.36	7.35	8.43	9.66	11.04	12.57	14.33	16.40	18.84	21.72
0.26	2.04	2.67	3.01	3.35	3.70	4.43	5.22	6.09	7.02	8.03	9.17	10.43	11.83	13.40	15.24	17.36	19.82
0.27	1.95	2.57	2.89	3.22	3.55	4.25	5.02	5.84	6.72	7.67	8.73	9.90	11.18	12.62	14.26	16.15	18.29
0.28	...	2.46	2.78	3.10	3.42	4.10	4.83	5.61	6.45	7.35	8.34	9.43	10.62	11.93	13.43	15.12	17.02
0.29	...	2.37	2.68	2.98	3.30	3.95	4.65	5.40	6.20	7.05	7.99	9.02	10.12	11.34	12.71	14.25	15.95
0.30	...	2.28	2.58	2.88	3.18	3.81	4.49	5.21	5.97	6.79	7.68	8.64	9.68	10.81	12.08	13.49	15.03
0.31	...	2.19	2.49	2.78	3.07	3.68	4.34	5.04	5.76	6.54	7.39	8.30	9.28	10.34	11.52	12.82	14.24
0.32	...	2.11	2.40	2.68	2.97	3.56	4.20	4.87	5.57	6.32	7.13	8.00	8.92	9.92	11.02	12.23	13.54
0.33	2.31	2.59	2.87	3.45	4.07	4.72	5.39	6.11	6.88	7.71	8.59	9.53	10.57	11.70	12.92
0.34	2.23	2.50	2.78	3.34	3.94	4.57	5.22	5.91	6.66	7.45	8.29	9.18	10.17	11.23	12.37
0.35	2.16	2.42	2.69	3.24	3.82	4.43	5.07	5.73	6.45	7.21	8.01	8.87	9.80	10.80	11.87
0.36	2.34	2.61	3.14	3.71	4.31	4.92	5.56	6.26	6.99	7.76	8.57	9.46	10.41	11.42
0.37	2.27	2.52	3.05	3.61	4.19	4.78	5.41	6.07	6.78	7.52	8.30	9.15	10.05	11.01
0.38	2.45	2.96	3.51	4.07	4.65	5.26	5.90	6.59	7.30	8.05	8.86	9.73	10.64
0.39	2.37	2.88	3.41	3.96	4.53	5.12	5.74	6.40	7.09	7.81	8.59	9.42	10.29
0.40	2.30	2.80	3.32	3.86	4.41	4.98	5.59	6.23	6.90	7.59	8.34	9.14	9.97

Table 3-9 Values of L for Pipe Sizes \geq NPS 42 and $<$ NPS 48 (Cont'd)

Depth, <i>d</i> , in.	Wall Thickness, <i>t</i> , in.																
	0.344	0.406	0.438	0.469	0.500	0.562	0.625	0.688	0.750	0.812	0.875	0.938	1.000	1.062	1.125	1.188	1.250
0.41	2.72	3.23	3.76	4.30	4.86	5.45	6.07	6.71	7.39	8.11	8.88	9.67
0.42	2.65	3.15	3.66	4.19	4.74	5.31	5.92	6.54	7.19	7.89	8.63	9.40
0.43	2.57	3.07	3.57	4.09	4.62	5.18	5.77	6.38	7.01	7.69	8.40	9.14
0.44	2.50	2.99	3.49	3.99	4.51	5.06	5.64	6.22	6.84	7.50	8.18	8.90
0.45	2.91	3.40	3.90	4.41	4.95	5.50	6.08	6.68	7.31	7.98	8.67
0.46	2.84	3.32	3.81	4.31	4.83	5.38	5.94	6.52	7.14	7.79	8.46
0.47	2.77	3.24	3.72	4.21	4.73	5.26	5.81	6.38	6.98	7.61	8.25
0.48	2.70	3.17	3.64	4.12	4.62	5.15	5.68	6.24	6.82	7.43	8.06
0.49	2.64	3.09	3.56	4.03	4.52	5.04	5.56	6.10	6.67	7.27	7.88
0.50	2.57	3.02	3.48	3.94	4.43	4.93	5.44	5.97	6.53	7.11	7.71
0.51	2.96	3.40	3.86	4.34	4.83	5.33	5.85	6.40	6.96	7.55
0.52	2.89	3.33	3.78	4.25	4.73	5.23	5.73	6.27	6.82	7.39
0.53	2.83	3.26	3.70	4.17	4.64	5.12	5.62	6.14	6.69	7.24
0.54	2.76	3.19	3.63	4.08	4.55	5.02	5.51	6.03	6.56	7.10
0.55	2.70	3.12	3.56	4.00	4.46	4.93	5.41	5.91	6.43	6.96
0.56	3.06	3.49	3.93	4.38	4.84	5.31	5.80	6.31	6.83
0.57	3.00	3.42	3.85	4.30	4.75	5.21	5.69	6.19	6.70
0.58	2.94	3.35	3.78	4.22	4.66	5.12	5.59	6.08	6.58
0.59	2.88	3.29	3.71	4.14	4.58	5.03	5.49	5.98	6.46
0.60	2.82	3.22	3.64	4.07	4.50	4.94	5.40	5.87	6.35
0.61	3.16	3.58	4.00	4.42	4.85	5.31	5.77	6.24
0.62	3.10	3.51	3.93	4.34	4.77	5.22	5.67	6.14
0.63	3.04	3.45	3.86	4.27	4.69	5.13	5.58	6.04
0.64	2.99	3.39	3.79	4.20	4.61	5.05	5.49	5.94
0.65	3.33	3.73	4.13	4.54	4.97	5.40	5.84
0.66	3.27	3.66	4.06	4.47	4.89	5.32	5.75
0.67	3.21	3.60	3.99	4.39	4.81	5.23	5.66
0.68	3.15	3.54	3.93	4.32	4.73	5.15	5.57
0.69	3.10	3.48	3.87	4.26	4.66	5.07	5.49
0.70	3.04	3.42	3.80	4.19	4.59	5.00	5.41
0.71	3.37	3.74	4.13	4.52	4.92	5.33
0.72	3.31	3.69	4.06	4.45	4.85	5.25
0.73	3.26	3.63	4.00	4.39	4.78	5.18
0.74	3.21	3.57	3.94	4.32	4.71	5.10
0.75	3.15	3.52	3.88	4.26	4.64	5.03
0.76	3.46	3.82	4.20	4.58	4.96

Table 3-9 Values of L for Pipe Sizes \geq NPS 42 and $<$ NPS 48 (Cont'd)

Depth, d , in.	Wall Thickness, t , in.													
	0.344	0.406	0.438	0.469	0.500	0.562	0.625	0.688	0.750	0.812	0.875	0.938	1.000	1.062
0.77	3.41	3.77
0.78	3.36	3.71
0.79	3.30	3.66
0.80	3.25	3.60
0.81	3.55
0.82	3.50
0.83	3.45
0.84	3.40
0.85
0.86
0.87
0.88
0.89
0.90
0.91
0.92
0.93
0.94
0.95
0.96
0.97
0.98
0.99
1.00

Table 3-9M Values of L for Pipe Sizes ≥ 1 066 mm and < 1 219 mm O.D.

Depth, <i>d</i> , mm	Wall Thickness, <i>t</i> , mm																
	8.7	10.3	11.1	11.9	12.7	14.3	15.9	17.5	19.1	20.6	22.2	23.8	25.4	27.0	28.6	30.2	31.8
0.8	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
1.0	432.5	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
1.3	432.5	469.9	488.1	505.0	521.5	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
1.5	432.5	469.9	488.1	505.0	521.5	552.8	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
1.8	277.7	469.9	488.1	505.0	521.5	552.8	583.0	611.7	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
2.0	211.6	326.3	420.4	505.0	521.5	552.8	583.0	611.7	638.7	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
2.3	174.5	251.4	306.4	376.0	471.2	552.8	583.0	611.7	638.7	664.5	689.8	No limit	No limit	No limit	No limit	No limit	No limit
2.5	150.3	208.4	246.9	292.3	348.9	519.7	583.0	611.7	638.7	664.5	689.8	714.2	737.5	No limit	No limit	No limit	No limit
2.8	133.0	180.1	209.8	243.4	283.2	390.5	570.0	611.7	638.7	664.5	689.8	714.2	737.5	760.0	No limit	No limit	No limit
3.0	119.8	159.7	184.1	210.8	241.5	319.1	433.4	611.7	638.7	664.5	689.8	714.2	737.5	760.0	782.2	803.8	No limit
3.3	109.4	144.2	165.0	187.4	212.4	273.1	356.1	475.5	638.7	664.5	689.8	714.2	737.5	760.0	782.2	803.8	824.5
3.6	100.8	131.9	150.1	169.4	190.7	240.8	305.7	392.7	514.4	664.5	689.8	714.2	737.5	760.0	782.2	803.8	824.5
3.8	93.6	121.9	138.1	155.2	173.8	216.6	270.0	338.2	427.3	552.4	689.8	714.2	737.5	760.0	782.2	803.8	824.5
4.1	87.5	113.4	128.2	143.6	160.2	197.6	243.2	299.3	369.3	461.4	592.0	714.2	737.5	760.0	782.2	803.8	824.5
4.3	82.1	106.2	119.8	133.9	148.9	182.3	222.2	269.9	327.5	400.0	496.8	630.8	737.5	760.0	782.2	803.8	824.5
4.6	77.3	99.9	112.6	125.5	139.3	169.6	205.2	246.8	295.8	355.5	431.9	531.7	666.3	760.0	782.2	803.8	824.5
4.8	73.1	94.4	106.2	118.3	131.0	158.9	191.0	228.1	270.8	321.6	384.5	463.5	564.4	701.0	782.2	803.8	824.5
5.1	69.3	89.5	100.6	111.9	123.8	149.6	179.1	212.6	250.5	294.8	348.3	413.4	493.4	596.5	737.6	803.8	824.5
5.3	65.8	85.0	95.6	106.3	117.5	141.6	168.8	199.4	233.6	272.9	319.5	374.9	441.0	523.0	630.0	773.6	824.5
5.6	62.6	81.0	91.1	101.2	111.8	134.4	159.8	188.1	219.3	254.7	296.0	344.2	400.5	468.4	553.8	663.1	806.1
5.8	59.6	77.3	87.0	96.6	106.7	128.1	151.9	178.2	206.9	239.2	276.4	319.1	368.1	425.9	496.7	584.3	693.8
6.1	56.9	74.0	83.2	92.4	102.0	122.4	144.8	169.4	196.2	225.9	259.7	298.2	341.6	391.9	452.3	524.9	612.9
6.4	54.3	70.8	79.7	88.6	97.8	117.2	138.5	161.7	186.7	214.2	245.4	280.4	319.3	363.9	416.5	478.5	551.7
6.6	51.9	67.9	76.5	85.0	93.9	112.4	132.7	154.7	178.2	204.0	232.8	265.0	300.4	340.5	387.0	441.0	503.5
6.9	49.6	65.2	73.5	81.7	90.2	108.1	127.5	148.3	170.6	194.8	221.8	251.5	284.0	320.4	362.3	410.1	464.6
7.1	...	62.6	70.7	78.7	86.9	104.0	122.6	142.6	163.7	186.6	211.9	239.6	269.7	303.1	341.1	384.1	432.3
7.4	...	60.2	68.0	75.8	83.7	100.3	118.2	137.3	157.4	179.1	203.0	229.0	257.1	288.0	322.8	361.8	405.2
7.6	...	57.9	65.5	73.1	80.8	96.8	114.1	132.4	151.7	172.4	195.0	219.5	245.8	274.6	306.8	342.5	381.9
7.9	...	55.7	63.2	70.5	78.0	93.6	110.2	127.9	146.4	166.1	187.7	210.9	235.7	262.6	292.6	325.6	361.7
8.1	...	53.6	60.9	68.1	75.4	90.5	106.6	123.7	141.5	160.4	181.0	203.1	226.5	251.9	279.9	310.7	343.9
8.4	58.8	65.8	72.9	87.6	103.3	119.8	136.9	155.1	174.8	195.9	218.2	242.2	268.6	297.3	328.2
8.6	56.7	63.6	70.6	84.9	100.1	116.1	132.7	150.2	169.1	189.3	210.5	233.3	258.2	285.3	314.2
8.9	54.8	61.5	68.3	82.3	97.1	112.6	128.7	145.6	163.8	183.2	203.5	225.2	248.9	274.4	301.6
9.1	59.5	66.2	79.9	94.3	109.4	125.0	141.3	158.9	177.5	197.0	217.7	240.3	264.5	290.1
9.4	57.6	64.1	77.5	91.6	106.3	121.4	137.3	154.3	172.2	190.9	210.8	232.3	255.4	279.7
9.7	62.2	75.3	89.1	103.4	118.1	133.5	150.0	167.3	185.3	204.4	225.0	247.0	270.2
9.9	60.3	73.1	86.6	100.6	115.0	129.9	145.9	162.7	180.1	198.5	218.3	239.3	261.4
10.2	58.4	71.1	84.3	98.0	112.0	126.5	142.0	158.3	175.1	192.9	211.9	232.1	253.3

Table 3-9M Values of L for Pipe Sizes $\geq 1\ 066$ mm and $< 1\ 219$ mm O.D. (Cont'd)

Depth, <i>d</i> , mm	Wall Thickness, <i>t</i> , mm																
	8.7	10.3	11.1	11.9	12.7	14.3	15.9	17.5	19.1	20.6	22.2	23.8	25.4	27.0	28.6	30.2	31.8
10.4	69.1	82.1	95.5	109.1	123.3	138.4	154.2	170.5	187.7	206.0	225.5	245.7
10.7	67.2	79.9	93.0	106.4	120.3	135.0	150.3	166.1	182.7	200.5	219.2	238.7
10.9	65.4	77.9	90.7	103.8	117.4	131.7	146.6	162.0	178.1	195.3	213.4	232.1
11.2	63.6	75.9	88.5	101.3	114.6	128.6	143.1	158.1	173.7	190.4	207.9	226.0
11.4	74.0	86.4	99.0	111.9	125.6	139.8	154.4	169.6	185.8	202.7	220.2
11.7	72.2	84.3	96.7	109.4	122.8	136.6	150.9	165.7	181.4	197.8	214.8
11.9	70.4	82.4	94.5	106.9	120.0	133.6	147.5	161.9	177.2	193.2	209.7
12.2	68.6	80.5	92.4	104.6	117.4	130.7	144.3	158.4	173.3	188.8	204.8
12.4	67.0	78.6	90.3	102.3	114.9	127.9	141.2	155.0	169.5	184.7	200.2
12.7	65.3	76.8	88.3	100.2	112.5	125.3	138.3	151.7	165.9	180.7	195.8
13.0	75.1	86.4	98.1	110.2	122.7	135.5	148.6	162.5	176.9	191.7
13.2	73.4	84.6	96.0	108.0	120.3	132.7	145.6	159.2	173.3	187.7
13.5	71.8	82.8	94.1	105.8	117.9	130.1	142.8	156.1	169.8	183.9
13.7	70.2	81.1	92.2	103.7	115.6	127.6	140.0	153.0	166.5	180.2
14.0	68.6	79.4	90.3	101.7	113.4	125.2	137.4	150.1	163.3	176.8
14.2	77.7	88.5	99.8	111.2	122.9	134.8	147.3	160.3	173.4
14.5	76.1	86.8	97.9	109.2	120.6	132.4	144.7	157.3	170.2
14.7	74.6	85.1	96.0	107.2	118.4	130.0	142.1	154.5	167.1
15.0	73.1	83.5	94.2	105.2	116.3	127.7	139.6	151.8	164.2
15.2	71.6	81.9	92.5	103.3	114.3	125.4	137.1	149.1	161.3
15.5	80.3	90.8	101.5	112.3	123.3	134.8	146.6	158.6
15.7	78.8	89.2	99.7	110.3	121.2	132.5	144.1	155.9
16.0	77.3	87.6	98.0	108.5	119.2	130.3	141.8	153.3
16.3	75.8	86.0	96.3	106.6	117.2	128.2	139.4	150.8
16.5	84.5	94.7	104.9	115.3	126.1	137.2	148.4
16.8	83.0	93.0	103.1	113.4	124.1	135.0	146.1
17.0	81.5	91.5	101.4	111.6	122.1	132.9	143.8
17.3	80.1	89.9	99.8	109.8	120.2	130.9	141.6
17.5	78.7	88.4	98.2	108.1	118.4	128.9	139.4
17.8	77.3	87.0	96.6	106.4	116.6	126.9	137.4
18.0	85.6	95.1	104.8	114.8	125.1	135.3
18.3	84.1	93.6	103.2	113.1	123.2	133.4
18.5	82.8	92.1	101.6	111.4	121.4	131.4
18.8	81.4	90.7	100.1	109.8	119.7	129.6
19.1	80.1	89.3	98.6	108.2	118.0	127.7
19.3	87.9	97.1	106.6	116.3	126.0

Table 3-9M Values of L for Pipe Sizes $\geq 1\ 066$ mm and $< 1\ 219$ mm O.D. (Cont'd)

Depth, d , mm	Wall Thickness, t , mm																
	8.7	10.3	11.1	11.9	12.7	14.3	15.9	17.5	19.1	20.6	22.2	23.8	25.4	27.0	28.6	30.2	31.8
19.6	86.6	95.7	105.1	114.7	124.2
19.8	85.2	94.3	103.6	113.1	122.5
20.1	83.9	92.9	102.1	111.5	120.9
20.3	82.7	91.5	100.7	110.0	119.2
20.6	90.2	99.3	108.5	117.6
20.8	88.9	97.9	107.0	116.1
21.1	87.6	96.5	105.6	114.5
21.3	86.4	95.2	104.1	113.1
21.6	93.9	102.8	111.6
21.8	92.6	101.4	110.1
22.1	91.3	100.1	108.7
22.4	90.1	98.7	107.3
22.6	88.9	97.5	106.0
22.9	87.7	96.2	104.6
23.1	94.9	103.3
23.4	93.7	102.0
23.6	92.5	100.8
23.9	91.3	99.5
24.1	90.1	98.3
24.4	97.1
24.6	95.9
24.9	94.7
25.1	93.5
25.4	92.4

Table 3-10 Values of L for Pipe Sizes \geq NPS 48 and $<$ NPS 52

Depth, <i>d</i> , in.	Wall Thickness, <i>t</i> , in.																
	0.344	0.406	0.438	0.469	0.500	0.562	0.625	0.688	0.750	0.812	0.875	0.938	1.000	1.062	1.125	1.188	1.250
0.03	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
0.04	18.20	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
0.05	18.20	19.78	20.54	21.26	21.95	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
0.06	18.20	19.78	20.54	21.26	21.95	23.27	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
0.07	11.69	19.78	20.54	21.26	21.95	23.27	24.54	25.74	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
0.08	8.91	13.73	17.69	21.26	21.95	23.27	24.54	25.74	26.88	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
0.09	7.35	10.58	12.89	15.82	19.83	23.27	24.54	25.74	26.88	27.97	29.03	No limit	No limit	No limit	No limit	No limit	No limit
0.10	6.33	8.77	10.39	12.30	14.69	21.87	24.54	25.74	26.88	27.97	29.03	30.06	31.04	No limit	No limit	No limit	No limit
0.11	5.60	7.58	8.83	10.24	11.92	16.44	23.99	25.74	26.88	27.97	29.03	30.06	31.04	31.99	No limit	No limit	No limit
0.12	5.04	6.72	7.75	8.87	10.16	13.43	18.24	25.74	26.88	27.97	29.03	30.06	31.04	31.99	32.92	33.83	No limit
0.13	4.60	6.07	6.94	7.89	8.94	11.49	14.99	20.01	26.88	27.97	29.03	30.06	31.04	31.99	32.92	33.83	34.70
0.14	4.24	5.55	6.32	7.13	8.03	10.13	12.87	16.53	21.65	27.97	29.03	30.06	31.04	31.99	32.92	33.83	34.70
0.15	3.94	5.13	5.81	6.53	7.32	9.11	11.36	14.23	17.99	23.25	29.03	30.06	31.04	31.99	32.92	33.83	34.70
0.16	3.68	4.77	5.40	6.04	6.74	8.32	10.24	12.60	15.54	19.42	24.92	30.06	31.04	31.99	32.92	33.83	34.70
0.17	3.46	4.47	5.04	5.63	6.27	7.67	9.35	11.36	13.78	16.84	20.91	26.55	31.04	31.99	32.92	33.83	34.70
0.18	3.26	4.21	4.74	5.28	5.86	7.14	8.63	10.39	12.45	14.96	18.18	22.38	28.04	31.99	32.92	33.83	34.70
0.19	3.08	3.97	4.47	4.98	5.52	6.69	8.04	9.60	11.40	13.54	16.18	19.51	23.75	29.51	32.92	33.83	34.70
0.20	2.92	3.77	4.24	4.71	5.21	6.30	7.54	8.95	10.54	12.41	14.66	17.40	20.77	25.10	31.05	33.83	34.70
0.21	2.77	3.58	4.02	4.47	4.94	5.96	7.10	8.39	9.83	11.49	13.45	15.78	18.56	22.01	26.52	32.56	34.70
0.22	2.63	3.41	3.83	4.26	4.71	5.66	6.73	7.91	9.23	10.72	12.46	14.49	16.86	19.71	23.31	27.91	33.93
0.23	2.51	3.26	3.66	4.07	4.49	5.39	6.39	7.50	8.71	10.07	11.63	13.43	15.49	17.93	20.91	24.59	29.20
0.24	2.39	3.11	3.50	3.89	4.29	5.15	6.10	7.13	8.26	9.51	10.93	12.55	14.38	16.49	19.03	22.09	25.80
0.25	2.29	2.98	3.35	3.73	4.12	4.93	5.83	6.80	7.86	9.02	10.33	11.80	13.44	15.32	17.53	20.14	23.22
0.26	2.18	2.86	3.22	3.58	3.95	4.73	5.59	6.51	7.50	8.58	9.80	11.15	12.64	14.33	16.29	18.56	21.19
0.27	2.09	2.74	3.09	3.44	3.80	4.55	5.36	6.24	7.18	8.20	9.33	10.59	11.95	13.49	15.25	17.26	19.55
0.28	...	2.63	2.97	3.31	3.66	4.38	5.16	6.00	6.89	7.85	8.92	10.09	11.35	12.76	14.36	16.17	18.20
0.29	...	2.53	2.86	3.19	3.52	4.22	4.97	5.78	6.63	7.54	8.54	9.64	10.82	12.12	13.59	15.23	17.05
0.30	...	2.44	2.76	3.08	3.40	4.08	4.80	5.57	6.38	7.25	8.21	9.24	10.35	11.56	12.91	14.42	16.07
0.31	...	2.34	2.66	2.97	3.28	3.94	4.64	5.38	6.16	6.99	7.90	8.88	9.92	11.05	12.32	13.71	15.22
0.32	...	2.26	2.56	2.87	3.17	3.81	4.49	5.21	5.95	6.75	7.62	8.55	9.53	10.60	11.78	13.08	14.48
0.33	2.47	2.77	3.07	3.69	4.35	5.04	5.76	6.53	7.36	8.25	9.18	10.19	11.30	12.51	13.81
0.34	2.39	2.68	2.97	3.57	4.21	4.89	5.58	6.32	7.12	7.97	8.86	9.82	10.87	12.01	13.22
0.35	2.31	2.59	2.88	3.46	4.09	4.74	5.42	6.13	6.90	7.71	8.56	9.48	10.47	11.55	12.69
0.36	2.50	2.79	3.36	3.97	4.60	5.26	5.95	6.69	7.47	8.29	9.16	10.11	11.13	12.21

Table 3-10 Values of L for Pipe Sizes \geq NPS 48 and $<$ NPS 52 (Cont'd)

Depth, d , in.	Wall Thickness, t , in.													
	0.344	0.406	0.438	0.469	0.500	0.562	0.625	0.688	0.750	0.812	0.875	0.938	1.000	1.062
0.37	2.42	2.70	3.26	3.86	4.47	5.11	5.78	6.49	7.25	8.04	8.87
0.38	2.62	3.17	3.75	4.35	4.97	5.62	6.31	7.04	7.80	8.60
0.39	2.54	3.08	3.65	4.23	4.84	5.47	6.14	6.85	7.58	8.35
0.40	2.46	2.99	3.55	4.12	4.71	5.33	5.98	6.66	7.37	8.12
0.41	2.91	3.45	4.02	4.59	5.19	5.83	6.49	7.18	7.90
0.42	2.83	3.36	3.92	4.48	5.06	5.68	6.33	6.99	7.69
0.43	2.75	3.28	3.82	4.37	4.94	5.54	6.17	6.82	7.50
0.44	2.68	3.19	3.73	4.26	4.82	5.41	6.02	6.65	7.31
0.45	3.11	3.64	4.16	4.71	5.29	5.88	6.50	7.14
0.46	3.04	3.55	4.07	4.60	5.17	5.75	6.35	6.97
0.47	2.96	3.47	3.98	4.50	5.05	5.62	6.21	6.82
0.48	2.89	3.39	3.89	4.40	4.94	5.50	6.07	6.67
0.49	2.82	3.31	3.80	4.31	4.84	5.39	5.94	6.52
0.50	2.75	3.23	3.72	4.22	4.74	5.27	5.82	6.39
0.51	3.16	3.64	4.13	4.64	5.17	5.70	6.26
0.52	3.09	3.56	4.04	4.54	5.06	5.59	6.13
0.53	3.02	3.48	3.96	4.45	4.96	5.48	6.01
0.54	2.95	3.41	3.88	4.37	4.87	5.37	5.89
0.55	2.89	3.34	3.80	4.28	4.77	5.27	5.78
0.56	3.27	3.73	4.20	4.68	5.17	5.67
0.57	3.20	3.65	4.12	4.60	5.08	5.57
0.58	3.14	3.58	4.04	4.51	4.98	5.47
0.59	3.07	3.51	3.97	4.43	4.90	5.37
0.60	3.01	3.45	3.89	4.35	4.81	5.28
0.61	3.38	3.82	4.27	4.73	5.19
0.62	3.32	3.75	4.20	4.64	5.10
0.63	3.25	3.69	4.12	4.57	5.02
0.64	3.19	3.62	4.05	4.49	4.93
0.65	3.55	3.98	4.41	4.85
0.66	3.49	3.92	4.34	4.77

Table 3-10 Values of L for Pipe Sizes \geq NPS 48 and $<$ NPS 52 (Cont'd)

Depth, d , in.	Wall Thickness, t , in.													
	0.344	0.406	0.438	0.469	0.500	0.562	0.625	0.688	0.750	0.812	0.875	0.938	1.000	1.062
0.67	3.43	3.85	4.27	4.70
0.68	3.37	3.79	4.20	4.62
0.69	3.31	3.72	4.13	4.55
0.70	3.25	3.66	4.07	4.48
0.71	3.60	4.00	4.41
0.72	3.54	3.94	4.34
0.73	3.48	3.88	4.28
0.74	3.43	3.82	4.21
0.75	3.37	3.76	4.15
0.76	3.70	4.09
0.77	3.64	4.03
0.78	3.59	3.97
0.79	3.53	3.91
0.80	3.48	3.85
0.81	3.80
0.82	3.74
0.83	3.69
0.84	3.63
0.85
0.86
0.87
0.88
0.89
0.90

Table 3-10M Values of L for Pipe Sizes ≥ 1 219 mm and < 1 320 mm O.D.

Depth, <i>d</i> , mm	Wall Thickness, <i>t</i> , mm																
	8.7	10.3	11.1	11.9	12.7	14.3	15.9	17.5	19.1	20.6	22.2	23.8	25.4	27.0	28.6	30.2	31.8
0.8	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
1.0	462.4	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
1.3	462.4	502.3	521.8	539.9	557.5	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
1.5	462.4	502.3	521.8	539.9	557.5	591.0	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
1.8	296.9	502.3	521.8	539.9	557.5	591.0	623.3	653.9	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
2.0	226.2	348.8	449.4	539.9	557.5	591.0	623.3	653.9	682.8	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
2.3	186.6	268.8	327.5	402.0	503.7	591.0	623.3	653.9	682.8	710.4	737.5	No limit	No limit	No limit	No limit	No limit	No limit
2.5	160.7	222.8	264.0	312.5	373.0	555.6	623.3	653.9	682.8	710.4	737.5	763.5	788.4	No limit	No limit	No limit	No limit
2.8	142.2	192.5	224.3	260.2	302.7	417.5	609.4	653.9	682.8	710.4	737.5	763.5	788.4	812.4	No limit	No limit	No limit
3.0	128.1	170.7	196.8	225.4	258.2	341.1	463.3	653.9	682.8	710.4	737.5	763.5	788.4	812.4	836.2	859.3	No limit
3.3	116.9	154.2	176.4	200.3	227.1	292.0	380.6	508.3	682.8	710.4	737.5	763.5	788.4	812.4	836.2	859.3	881.4
3.6	107.8	141.0	160.5	181.1	203.9	257.4	326.8	419.8	549.9	710.4	737.5	763.5	788.4	812.4	836.2	859.3	881.4
3.8	100.1	130.3	147.7	165.9	185.8	231.5	288.7	361.6	456.8	590.5	737.5	763.5	788.4	812.4	836.2	859.3	881.4
4.1	93.5	121.3	137.1	153.5	171.2	211.3	260.0	320.0	394.8	493.3	632.9	763.5	788.4	812.4	836.2	859.3	881.4
4.3	87.8	113.5	128.1	143.1	159.1	194.9	237.5	288.6	350.1	427.7	531.1	674.4	788.4	812.4	836.2	859.3	881.4
4.6	82.7	106.8	120.3	134.2	148.9	181.3	219.3	263.9	316.2	380.1	461.7	568.4	712.3	812.4	836.2	859.3	881.4
4.8	78.2	100.9	113.6	126.5	140.1	169.9	204.2	243.9	289.5	343.8	411.1	495.5	603.3	749.4	836.2	859.3	881.4
5.1	74.1	95.7	107.6	119.7	132.4	160.0	191.4	227.2	267.8	315.1	372.3	442.0	527.5	637.7	788.6	859.3	881.4
5.3	70.3	90.9	102.2	113.6	125.6	151.3	180.4	213.2	249.7	291.7	341.6	400.8	471.4	559.1	673.5	827.0	881.4
5.6	66.9	86.6	97.4	108.2	119.5	143.7	170.8	201.0	234.4	272.3	316.4	368.0	428.1	500.7	592.0	708.9	861.8
5.8	63.8	82.7	93.0	103.3	114.0	136.9	162.4	190.5	221.2	255.7	295.5	341.2	393.5	455.3	531.0	624.6	741.7
6.1	60.8	79.1	88.9	98.8	109.1	130.8	154.8	181.1	209.7	241.5	277.7	318.8	365.1	418.9	483.5	561.2	655.3
6.4	58.1	75.7	85.2	94.7	104.5	125.3	148.0	172.8	199.6	229.0	262.3	299.7	341.4	389.0	445.2	511.5	589.8
6.6	55.5	72.6	81.8	90.9	100.3	120.2	141.9	165.3	190.5	218.0	248.9	283.3	321.1	364.0	413.8	471.5	538.3
6.9	53.0	69.7	78.5	87.4	96.5	115.5	136.3	158.6	182.4	208.3	237.1	268.9	303.7	342.6	387.3	438.4	496.7
7.1	...	66.9	75.5	84.1	92.9	111.2	131.1	152.4	175.0	199.5	226.5	256.2	288.4	324.1	364.7	410.6	462.2
7.4	...	64.3	72.7	81.0	89.5	107.2	126.4	146.8	168.3	191.5	217.0	244.9	274.8	307.9	345.1	386.8	433.1
7.6	...	61.9	70.0	78.1	86.4	103.5	121.9	141.5	162.2	184.3	208.5	234.7	262.8	293.5	328.0	366.2	408.2
7.9	...	59.6	67.5	75.4	83.4	100.0	117.8	136.7	156.5	177.6	200.6	225.5	252.0	280.8	312.8	348.1	386.6
8.1	...	57.3	65.1	72.8	80.6	96.8	114.0	132.2	151.3	171.5	193.5	217.1	242.2	269.3	299.3	332.1	367.7
8.4	62.8	70.3	78.0	93.7	110.4	128.0	146.4	165.8	186.9	209.4	233.2	258.9	287.1	317.8	350.9
8.6	60.7	68.0	75.4	90.8	107.0	124.1	141.8	160.6	180.8	202.4	225.1	249.4	276.1	305.0	335.9
8.9	58.6	65.8	73.0	88.0	103.8	120.4	137.6	155.7	175.1	195.8	217.5	240.7	266.0	293.3	322.4
9.1	63.6	70.8	85.4	100.8	116.9	133.6	151.1	169.9	189.8	210.6	232.8	256.8	282.7	310.2

Table 3-10M Values of L for Pipe Sizes ≥ 1 219 mm and < 1 320 mm O.D. (Cont'd)

Depth, d , mm	Wall Thickness, t , mm																
	8.7	10.3	11.1	11.9	12.7	14.3	15.9	17.5	19.1	20.6	22.2	23.8	25.4	27.0	28.6	30.2	31.8
9.4	61.6	68.6	82.9	97.9	113.7	129.8	146.8	164.9	184.1	204.1	225.4	248.4	273.0	299.0
9.7	66.5	80.5	95.2	110.5	126.3	142.7	160.3	178.9	198.1	218.5	240.6	264.1	288.8
9.9	64.4	78.2	92.6	107.6	122.9	138.9	156.0	173.9	192.5	212.2	233.3	255.8	279.4
10.2	62.5	76.0	90.1	104.7	119.7	135.3	151.9	169.2	187.2	206.2	226.6	248.2	270.7
10.4	73.9	87.7	102.0	116.7	131.8	148.0	164.9	182.3	200.6	220.3	241.0	262.7
10.7	71.9	85.5	99.5	113.8	128.6	144.3	160.7	177.6	195.4	214.3	234.4	255.2
10.9	69.9	83.3	97.0	111.0	125.5	140.8	156.8	173.2	190.4	208.8	228.1	248.2
11.2	68.0	81.1	94.6	108.3	122.5	137.5	153.0	169.0	185.7	203.5	222.2	241.6
11.4	79.1	92.4	105.8	119.7	134.3	149.5	165.1	181.3	198.6	216.7	235.4
11.7	77.1	90.2	103.3	116.9	131.2	146.1	161.3	177.1	193.9	211.5	229.6
11.9	75.2	88.0	101.0	114.3	128.3	142.8	157.7	173.1	189.5	206.5	224.1
12.2	73.4	86.0	98.7	111.8	125.5	139.7	154.2	169.3	185.2	201.9	218.9
12.4	71.6	84.0	96.5	109.4	122.9	136.8	151.0	165.7	181.2	197.4	214.0
12.7	69.9	82.1	94.4	107.1	120.3	133.9	147.8	162.2	177.4	193.2	209.3
13.0	80.3	92.4	104.8	117.8	131.2	144.8	158.9	173.7	189.1	204.9
13.2	78.5	90.4	102.7	115.4	128.6	141.9	155.7	170.2	185.3	200.6
13.5	76.7	88.5	100.6	113.1	126.0	139.1	152.6	166.8	181.6	196.6
13.7	75.0	86.7	98.5	110.9	123.6	136.4	149.7	163.6	178.0	192.7
14.0	73.4	84.9	96.6	108.7	121.2	133.8	146.9	160.5	174.6	189.0
14.2	83.1	94.7	106.6	118.9	131.3	144.1	157.5	171.3	185.4
14.5	81.4	92.8	104.6	116.7	128.9	141.5	154.6	168.2	182.0
14.7	79.7	91.0	102.6	114.6	126.6	139.0	151.9	165.2	178.7
15.0	78.1	89.2	100.7	112.5	124.3	136.5	149.2	162.3	175.5
15.2	76.5	87.5	98.9	110.5	122.1	134.1	146.6	159.4	172.5
15.5	85.9	97.1	108.5	120.0	131.8	144.1	156.7	169.5
15.7	84.2	95.3	106.6	118.0	129.6	141.7	154.1	166.7
16.0	82.6	93.6	104.8	116.0	127.4	139.3	151.5	163.9
16.3	81.1	91.9	102.9	114.0	125.3	137.0	149.1	161.2
16.5	90.3	101.2	112.1	123.2	134.8	146.7	158.7
16.8	88.7	99.5	110.3	121.3	132.7	144.4	156.2

Table 3-10M Values of L for Pipe Sizes ≥ 1 219 mm and < 1 320 mm O.D. (Cont'd)

Depth, d , mm	Wall Thickness, t , mm																
	8.7	10.3	11.1	11.9	12.7	14.3	15.9	17.5	19.1	20.6	22.2	23.8	25.4	27.0	28.6	30.2	31.8
17.0	87.1	97.8	108.5	119.3	130.6	142.1	153.7
17.3	85.6	96.2	106.7	117.4	128.5	139.9	151.4
17.5	84.1	94.6	105.0	115.6	126.6	137.8	149.1
17.8	82.7	93.0	103.3	113.8	124.6	135.7	146.9
18.0	91.5	101.7	112.0	122.8	133.7	144.7
18.3	90.0	100.1	110.3	120.9	131.7	142.6
18.5	88.5	98.5	108.6	119.1	129.8	140.5
18.8	87.0	97.0	107.0	117.4	127.9	138.5
19.1	85.6	95.5	105.4	115.7	126.1	136.6
19.3	94.0	103.8	114.0	124.3	134.7
19.6	92.5	102.3	112.4	122.6	132.8
19.8	91.1	100.8	110.7	120.9	131.0
20.1	89.7	99.3	109.2	119.2	129.2
20.3	88.4	97.9	107.6	117.6	127.5
20.6	96.4	106.1	115.9	125.8
20.8	95.0	104.7	114.4	124.1
21.1	93.7	103.2	112.8	122.5
21.3	92.3	101.8	111.3	120.9
21.6	100.4	109.8	119.3
21.8	99.0	108.4	117.8
22.1	97.6	107.0	116.2
22.4	96.3	105.6	114.8
22.6	95.0	104.2	113.3
22.9	93.7	102.8	111.9

Table 3-11 Values of L for Pipe Sizes \geq NPS 52 and $<$ NPS 56

Depth, <i>d</i> , in.	Wall Thickness, <i>t</i> , in.															
	0.406	0.438	0.469	0.500	0.562	0.625	0.688	0.750	0.812	0.875	0.938	1.000	1.062	1.125	1.188	1.250
0.04	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
0.05	20.58	21.38	22.12	22.84	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
0.06	20.58	21.38	22.12	22.84	24.22	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
0.07	20.58	21.38	22.12	22.84	24.22	25.54	26.80	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
0.08	14.29	18.42	22.12	22.84	24.22	25.54	26.80	27.98	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
0.09	11.01	13.42	16.47	20.64	24.22	25.54	26.80	27.98	29.11	30.22	No limit	No limit	No limit	No limit	No limit	No limit
0.10	9.13	10.82	12.81	15.28	22.77	25.54	26.80	27.98	29.11	30.22	31.29	29.55	No limit	No limit	No limit	No limit
0.11	7.89	9.19	10.66	12.41	17.11	24.97	26.80	27.98	29.11	30.22	31.29	29.55	33.29	No limit	No limit	No limit
0.12	7.00	8.06	9.24	10.58	13.98	18.99	26.80	27.98	29.11	30.22	31.29	32.31	33.29	34.27	35.21	No limit
0.13	6.32	7.23	8.21	9.31	11.96	15.60	20.83	27.98	29.11	30.22	31.29	32.31	33.29	34.27	35.21	36.12
0.14	5.78	6.58	7.42	8.36	10.55	13.39	17.20	22.54	29.11	30.22	31.29	32.31	33.29	34.27	35.21	36.12
0.15	5.34	6.05	6.80	7.61	9.49	11.83	14.82	18.72	24.20	30.22	31.29	32.31	33.29	34.27	35.21	36.12
0.16	4.97	5.62	6.29	7.02	8.66	10.65	13.11	16.18	20.21	25.93	31.29	32.31	33.29	34.27	35.21	36.12
0.17	4.65	5.25	5.86	6.52	7.99	9.73	11.82	14.35	17.52	21.76	27.63	32.31	33.29	34.27	35.21	36.12
0.18	4.38	4.93	5.50	6.10	7.43	8.99	10.81	12.96	15.58	18.92	23.29	29.19	33.29	34.27	35.21	36.12
0.19	4.14	4.65	5.18	5.74	6.96	8.37	9.99	11.86	14.09	16.85	20.31	24.72	30.71	34.27	35.21	36.12
0.20	3.92	4.41	4.90	5.43	6.56	7.84	9.31	10.97	12.91	15.26	18.11	21.62	26.13	32.31	35.21	36.12
0.21	3.73	4.19	4.66	5.15	6.20	7.39	8.73	10.23	11.95	14.00	16.42	19.32	22.91	27.60	33.89	36.12
0.22	3.55	3.99	4.43	4.90	5.89	7.00	8.24	9.61	11.16	12.97	15.08	17.54	20.52	24.26	29.05	35.31
0.23	3.39	3.81	4.23	4.67	5.61	6.65	7.80	9.07	10.48	12.11	13.98	16.13	18.66	21.76	25.60	30.39
0.24	3.24	3.64	4.05	4.47	5.36	6.34	7.42	8.59	9.89	11.38	13.06	14.96	17.17	19.81	23.00	26.85
0.25	3.10	3.49	3.88	4.28	5.13	6.07	7.08	8.18	9.39	10.75	12.28	13.99	15.94	18.25	20.96	24.17
0.26	2.97	3.35	3.73	4.11	4.92	5.81	6.78	7.81	8.93	10.20	11.61	13.16	14.91	16.95	19.32	22.06
0.27	2.85	3.22	3.58	3.95	4.73	5.58	6.50	7.47	8.53	9.71	11.02	12.44	14.04	15.87	17.97	20.35
0.28	2.74	3.10	3.45	3.81	4.56	5.37	6.25	7.17	8.17	9.28	10.50	11.82	13.28	14.94	16.83	18.94
0.29	2.64	2.98	3.32	3.67	4.39	5.18	6.01	6.90	7.85	8.89	10.03	11.26	12.62	14.14	15.85	17.75
0.30	2.54	2.87	3.20	3.54	4.24	5.00	5.80	6.64	7.55	8.54	9.62	10.77	12.03	13.44	15.01	16.73
0.31	2.44	2.77	3.09	3.42	4.10	4.83	5.60	6.41	7.28	8.22	9.24	10.32	11.51	12.82	14.26	15.84
0.32	2.35	2.67	2.98	3.30	3.97	4.67	5.42	6.20	7.03	7.93	8.90	9.92	11.03	12.26	13.61	15.07
0.33	...	2.57	2.88	3.19	3.84	4.52	5.25	6.00	6.80	7.66	8.58	9.56	10.61	11.76	13.02	14.38
0.34	...	2.49	2.79	3.09	3.72	4.39	5.09	5.81	6.58	7.41	8.29	9.22	10.22	11.31	12.50	13.76

Table 3-11 Values of L for Pipe Sizes \geq NPS 52 and $<$ NPS 56 (Cont'd)

Depth, <i>d</i> , in.	Wall Thickness, <i>t</i> , in.															
	0.406	0.438	0.469	0.500	0.562	0.625	0.688	0.750	0.812	0.875	0.938	1.000	1.062	1.125	1.188	1.250
0.35	...	2.40	2.69	2.99	3.61	4.26	4.93	5.64	6.38	7.18	8.02	8.91	9.86	10.90	12.02	13.21
0.36	2.61	2.90	3.50	4.13	4.79	5.47	6.19	6.96	7.78	8.63	9.54	10.52	11.59	12.71
0.37	2.52	2.81	3.40	4.01	4.66	5.32	6.01	6.76	7.55	8.36	9.24	10.18	11.19	12.25
0.38	2.72	3.30	3.90	4.53	5.17	5.85	6.57	7.33	8.12	8.95	9.86	10.82	11.83
0.39	2.64	3.20	3.80	4.41	5.04	5.69	6.39	7.13	7.89	8.69	9.56	10.48	11.45
0.40	2.56	3.11	3.69	4.29	4.90	5.54	6.22	6.94	7.67	8.45	9.28	10.17	11.09
0.41	3.03	3.60	4.18	4.78	5.40	6.06	6.76	7.47	8.22	9.03	9.88	10.76
0.42	2.94	3.50	4.08	4.66	5.27	5.91	6.59	7.28	8.01	8.78	9.60	10.46
0.43	2.86	3.41	3.97	4.55	5.14	5.77	6.42	7.10	7.80	8.56	9.35	10.17
0.44	2.79	3.33	3.88	4.44	5.02	5.63	6.27	6.93	7.61	8.34	9.11	9.90
0.45	3.24	3.78	4.33	4.90	5.50	6.13	6.76	7.43	8.14	8.88	9.65
0.46	3.16	3.69	4.23	4.79	5.38	5.99	6.61	7.26	7.95	8.67	9.41
0.47	3.08	3.61	4.14	4.68	5.26	5.85	6.46	7.09	7.76	8.46	9.18
0.48	3.01	3.52	4.05	4.58	5.14	5.73	6.32	6.94	7.59	8.27	8.97
0.49	2.93	3.44	3.96	4.48	5.03	5.60	6.19	6.79	7.43	8.09	8.77
0.50	2.86	3.37	3.87	4.39	4.93	5.49	6.06	6.65	7.27	7.92	8.58
0.51	3.29	3.79	4.30	4.83	5.38	5.93	6.51	7.12	7.75	8.40
0.52	3.22	3.71	4.21	4.73	5.27	5.81	6.38	6.97	7.59	8.22
0.53	3.14	3.63	4.12	4.64	5.16	5.70	6.25	6.84	7.44	8.06
0.54	3.07	3.55	4.04	4.54	5.06	5.59	6.13	6.70	7.29	7.90
0.55	3.01	3.48	3.96	4.46	4.97	5.48	6.02	6.58	7.16	7.74
0.56	3.41	3.88	4.37	4.87	5.38	5.91	6.45	7.02	7.60
0.57	3.34	3.80	4.29	4.78	5.28	5.80	6.34	6.89	7.46
0.58	3.27	3.73	4.21	4.69	5.19	5.69	6.22	6.77	7.32
0.59	3.20	3.66	4.13	4.61	5.10	5.59	6.11	6.65	7.19
0.60	3.14	3.59	4.05	4.53	5.01	5.50	6.01	6.53	7.07
0.61	3.52	3.98	4.45	4.92	5.40	5.90	6.42	6.95
0.62	3.45	3.91	4.37	4.83	5.31	5.81	6.31	6.83
0.63	3.39	3.84	4.29	4.75	5.22	5.71	6.21	6.72
0.64	3.32	3.77	4.22	4.67	5.13	5.62	6.11	6.61
0.65	3.70	4.15	4.59	5.05	5.52	6.01	6.50
0.66	3.63	4.08	4.52	4.97	5.44	5.92	6.40
0.67	3.57	4.01	4.44	4.89	5.35	5.82	6.30
0.68	3.51	3.94	4.37	4.81	5.27	5.73	6.20
0.69	3.45	3.87	4.30	4.74	5.19	5.65	6.11
0.70	3.39	3.81	4.23	4.66	5.11	5.56	6.02

Table 3-11 Values of L for Pipe Sizes \geq NPS 52 and $<$ NPS 56 (Cont'd)

Depth, <i>d</i> , in.	Wall Thickness, <i>t</i> , in.															
	0.406	0.438	0.469	0.500	0.562	0.625	0.688	0.750	0.812	0.875	0.938	1.000	1.062	1.125	1.188	1.250
0.71	3.75	4.17	4.59	5.03	5.48	5.93
0.72	3.69	4.10	4.52	4.95	5.40	5.84
0.73	3.63	4.04	4.45	4.88	5.32	5.76
0.74	3.57	3.97	4.38	4.81	5.24	5.68
0.75	3.51	3.91	4.32	4.74	5.17	5.60
0.76	3.85	4.25	4.67	5.09	5.52
0.77	3.79	4.19	4.60	5.02	5.44
0.78	3.73	4.13	4.54	4.95	5.37
0.79	3.68	4.07	4.47	4.88	5.29
0.80	3.62	4.01	4.41	4.82	5.22
0.81	3.95	4.35	4.75	5.15
0.82	3.89	4.29	4.69	5.08
0.83	3.84	4.23	4.62	5.02
0.84	3.78	4.17	4.56	4.95
0.85	4.11	4.50	4.89
0.86	4.06	4.44	4.83
0.87	4.00	4.38	4.76
0.88	3.95	4.33	4.70
0.89	3.89	4.27	4.64
0.90	3.84	4.21	4.58
0.91	4.16	4.53
0.92	4.10	4.47
0.93	4.05	4.41
0.94	4.00	4.36
0.95	3.95	4.31
0.96	4.25
0.97	4.20
0.98	4.15
0.99	4.10
1.00	4.05

Table 3-11M Values of L for Pipe Sizes ≥ 1 320 mm and < 1 422 mm O.D.

Depth, <i>d</i> , mm	Wall Thickness, <i>t</i> , mm															
	10.3	11.1	11.9	12.7	14.3	15.9	17.5	19.1	20.6	22.2	23.8	25.4	27.0	28.6	30.2	31.8
1.0	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
1.3	522.8	543.1	562.0	580.2	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
1.5	522.8	543.1	562.0	580.2	615.2	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
1.8	522.8	543.1	562.0	580.2	615.2	648.7	680.6	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
2.0	363.1	467.7	562.0	580.2	615.2	648.7	680.6	710.6	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
2.3	279.7	340.9	418.4	524.3	615.2	648.7	680.6	710.6	739.4	767.6	No limit	No limit	No limit	No limit	No limit	No limit
2.5	231.9	274.8	325.3	388.2	578.3	648.7	680.6	710.6	739.4	767.6	794.7	750.6	No limit	No limit	No limit	No limit
2.8	200.4	233.5	270.8	315.1	434.5	634.3	680.6	710.6	739.4	767.6	794.7	750.6	845.6	No limit	No limit	No limit
3.0	177.7	204.8	234.6	268.7	355.0	482.3	680.6	710.6	739.4	767.6	794.7	820.6	845.6	870.3	894.4	No limit
3.3	160.5	183.6	208.5	236.4	303.9	396.2	529.1	710.6	739.4	767.6	794.7	820.6	845.6	870.3	894.4	917.4
3.6	146.8	167.0	188.5	212.2	267.9	340.2	437.0	572.4	739.4	767.6	794.7	820.6	845.6	870.3	894.4	917.4
3.8	135.6	153.7	172.7	193.4	241.0	300.5	376.3	475.5	614.7	767.6	794.7	820.6	845.6	870.3	894.4	917.4
4.1	126.2	142.7	159.8	178.2	219.9	270.6	333.0	410.9	513.4	658.7	794.7	820.6	845.6	870.3	894.4	917.4
4.3	118.2	133.3	148.9	165.6	202.9	247.2	300.3	364.4	445.1	552.8	701.9	820.6	845.6	870.3	894.4	917.4
4.6	111.2	125.2	139.7	155.0	188.7	228.3	274.6	329.1	395.6	480.6	591.7	741.4	845.6	870.3	894.4	917.4
4.8	105.0	118.2	131.6	145.8	176.8	212.6	253.8	301.3	357.9	427.9	515.8	628.0	780.0	870.3	894.4	917.4
5.1	99.6	112.0	124.6	137.8	166.5	199.3	236.5	278.7	328.0	387.5	460.0	549.0	663.7	820.8	894.4	917.4
5.3	94.6	106.4	118.3	130.7	157.5	187.8	221.9	259.9	303.6	355.5	417.1	490.7	582.0	701.0	860.7	917.4
5.6	90.2	101.3	112.6	124.4	149.6	177.8	209.2	244.0	283.4	329.4	383.0	445.6	521.1	616.2	737.9	897.0
5.8	86.1	96.8	107.5	118.7	142.5	169.0	198.2	230.3	266.2	307.6	355.1	409.6	473.9	552.7	650.1	772.0
6.1	82.3	92.6	102.9	113.5	136.1	161.1	188.5	218.3	251.3	289.0	331.8	380.0	436.1	503.2	584.1	682.0
6.4	78.8	88.7	98.6	108.8	130.4	154.1	179.9	207.7	238.4	273.0	311.9	355.3	404.9	463.4	532.4	613.9
6.6	75.6	85.1	94.6	104.4	125.1	147.7	172.1	198.3	226.9	259.1	294.8	334.3	378.8	430.6	490.7	560.3
6.9	72.5	81.8	91.0	100.4	120.2	141.8	165.1	189.8	216.8	246.8	279.9	316.1	356.6	403.1	456.3	516.9
7.1	69.7	78.6	87.5	96.7	115.8	136.5	158.6	182.2	207.6	235.8	266.6	300.1	337.3	379.6	427.4	481.1
7.4	67.0	75.7	84.3	93.2	111.6	131.5	152.8	175.2	199.3	225.9	254.9	286.1	320.4	359.2	402.6	450.8
7.6	64.4	72.9	81.3	89.9	107.7	126.9	147.3	168.8	191.8	217.0	244.3	273.5	305.5	341.4	381.1	424.9
7.9	62.0	70.3	78.5	86.8	104.1	122.7	142.3	162.9	184.9	208.8	234.7	262.2	292.2	325.6	362.3	402.4
8.1	59.7	67.8	75.8	83.9	100.7	118.7	137.6	157.4	178.5	201.4	226.0	252.0	280.3	311.5	345.7	382.7
8.4	...	65.4	73.2	81.1	97.5	114.9	133.3	152.4	172.6	194.5	218.0	242.8	269.4	298.8	330.8	365.2
8.6	...	63.1	70.8	78.5	94.5	111.4	129.2	147.6	167.1	188.2	210.6	234.2	259.6	287.3	317.4	349.6

Table 3-11M Values of L for Pipe Sizes ≥ 1 320 mm and < 1 422 mm O.D. (Cont'd)

Depth, d , mm	Wall Thickness, t , mm															
	10.3	11.1	11.9	12.7	14.3	15.9	17.5	19.1	20.6	22.2	23.8	25.4	27.0	28.6	30.2	31.8
8.9	...	60.9	68.4	76.0	91.6	108.1	125.3	143.2	162.0	182.3	203.8	226.4	250.6	276.9	305.3	335.6
9.1	66.2	73.6	88.9	104.9	121.7	139.0	157.3	176.8	197.5	219.2	242.3	267.3	294.3	322.8
9.4	64.1	71.4	86.3	101.9	118.3	135.1	152.8	171.7	191.6	212.5	234.6	258.5	284.2	311.2
9.7	69.2	83.8	99.1	115.0	131.4	148.6	166.9	186.2	206.2	227.5	250.4	274.9	300.6
9.9	67.1	81.4	96.4	112.0	127.9	144.6	162.3	181.0	200.4	220.8	242.8	266.3	290.8
10.2	65.0	79.1	93.8	109.0	124.6	140.8	158.1	176.2	194.9	214.6	235.8	258.3	281.8
10.4	76.9	91.3	106.2	121.4	137.2	154.0	171.6	189.7	208.8	229.2	250.9	273.4
10.7	74.8	88.9	103.5	118.4	133.8	150.2	167.3	184.9	203.3	223.1	243.9	265.6
10.9	72.8	86.7	101.0	115.5	130.6	146.5	163.2	180.3	198.2	217.3	237.4	258.3
11.2	70.8	84.5	98.5	112.7	127.5	143.1	159.3	175.9	193.3	211.9	231.3	251.5
11.4	82.3	96.1	110.1	124.5	139.8	155.6	171.8	188.7	206.7	225.6	245.1
11.7	80.3	93.8	107.6	121.7	136.6	152.0	167.9	184.3	201.8	220.1	239.0
11.9	78.3	91.6	105.1	119.0	133.6	148.7	164.1	180.2	197.2	215.0	233.3
12.2	76.4	89.5	102.8	116.4	130.7	145.5	160.5	176.2	192.8	210.1	227.9
12.4	74.5	87.5	100.5	113.9	127.9	142.4	157.1	172.4	188.6	205.5	222.8
12.7	72.7	85.5	98.3	111.4	125.2	139.4	153.9	168.8	184.6	201.1	217.9
13.0	83.5	96.2	109.1	122.6	136.6	150.7	165.4	180.8	196.8	213.2
13.2	81.7	94.1	106.9	120.1	133.8	147.7	162.1	177.2	192.8	208.8
13.5	79.8	92.1	104.7	117.7	131.2	144.8	158.9	173.6	189.0	204.6
13.7	78.1	90.2	102.6	115.4	128.6	142.0	155.8	170.3	185.3	200.6
14.0	76.3	88.3	100.5	113.2	126.2	139.3	152.9	167.1	181.7	196.7
14.2	86.5	98.5	111.0	123.8	136.7	150.0	163.9	178.3	193.0
14.5	84.7	96.6	108.9	121.5	134.2	147.3	161.0	175.1	189.4
14.7	83.0	94.7	106.8	119.2	131.8	144.6	158.1	171.9	186.0
15.0	81.3	92.9	104.9	117.1	129.4	142.1	155.3	168.9	182.7
15.2	79.6	91.1	102.9	115.0	127.1	139.6	152.6	165.9	179.5
15.5	89.4	101.0	112.9	124.9	137.2	150.0	163.1	176.4
15.7	87.7	99.2	111.0	122.8	134.9	147.5	160.4	173.5
16.0	86.0	97.4	109.0	120.7	132.6	145.0	157.7	170.6
16.3	84.4	95.7	107.2	118.7	130.4	142.6	155.2	167.8
16.5	94.0	105.3	116.7	128.3	140.3	152.7	165.1
16.8	92.3	103.5	114.8	126.2	138.1	150.3	162.5
17.0	90.7	101.8	112.9	124.2	135.9	147.9	160.0
17.3	89.1	100.1	111.1	122.2	133.8	145.6	157.5
17.5	87.6	98.4	109.3	120.3	131.7	143.4	155.2
17.8	86.0	96.8	107.5	118.4	129.7	141.3	152.8

Table 3-11M Values of L for Pipe Sizes ≥ 1 320 mm and < 1 422 mm O.D. (Cont'd)

Depth, <i>d</i> , mm	Wall Thickness, <i>t</i> , mm															
	10.3	11.1	11.9	12.7	14.3	15.9	17.5	19.1	20.6	22.2	23.8	25.4	27.0	28.6	30.2	31.8
18.0	95.2	105.8	116.6	127.8	139.2	150.6
18.3	93.6	104.1	114.8	125.9	137.1	148.4
18.5	92.1	102.5	113.1	124.0	135.1	146.3
18.8	90.6	100.9	111.4	122.2	133.2	144.2
19.1	89.1	99.4	109.7	120.4	131.2	142.1
19.3	97.8	108.1	118.6	129.4	140.2
19.6	96.3	106.5	116.9	127.6	138.2
19.8	94.8	104.9	115.3	125.8	136.3
20.1	93.4	103.4	113.6	124.1	134.5
20.3	92.0	101.9	112.0	122.4	132.7
20.6	100.4	110.5	120.7	130.9
20.8	98.9	108.9	119.0	129.2
21.1	97.5	107.4	117.4	127.5
21.3	96.1	105.9	115.9	125.8
21.6	104.5	114.3	124.2
21.8	103.0	112.8	122.6
22.1	101.6	111.3	121.0
22.4	100.2	109.9	119.4
22.6	98.9	108.4	117.9
22.9	97.5	107.0	116.4
23.1	105.6	115.0
23.4	104.3	113.5
23.6	102.9	112.1
23.9	101.6	110.7
24.1	100.3	109.4
24.4	108.0
24.6	106.7
24.9	105.4
25.1	104.1
25.4	102.8

Table 3-12 Values of L for Pipe Sizes ≥ NPS 56 Through NPS 60

Depth, d, in.	Wall Thickness, t, in.															
	0.406	0.438	0.469	0.500	0.562	0.625	0.688	0.750	0.812	0.875	0.938	1.000	1.062	1.125	1.188	1.250
0.04	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
0.05	21.36	22.19	22.96	23.71	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
0.06	21.36	22.19	22.96	23.71	25.13	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
0.07	21.36	22.19	22.96	23.71	25.13	26.50	27.81	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
0.08	14.83	19.11	22.96	23.71	25.13	26.50	27.81	29.03	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
0.09	11.43	13.93	17.09	21.42	25.13	26.50	27.81	29.03	30.21	31.36	No limit	No limit	No limit	No limit	No limit	No limit
0.10	9.48	11.23	13.29	15.86	23.63	26.50	27.81	29.03	30.21	31.36	32.47	33.53	No limit	No limit	No limit	No limit
0.11	8.19	9.54	11.07	12.87	17.75	25.91	27.81	29.03	30.21	31.36	32.47	33.53	34.55	No limit	No limit	No limit
0.12	7.26	8.37	9.59	10.98	14.50	19.70	27.81	29.03	30.21	31.36	32.47	33.53	34.55	35.56	36.54	No limit
0.13	6.56	7.50	8.52	9.66	12.42	16.19	21.62	29.03	30.21	31.36	32.47	33.53	34.55	35.56	36.54	37.48
0.14	6.00	6.82	7.70	8.67	10.95	13.90	17.85	23.39	30.21	31.36	32.47	33.53	34.55	35.56	36.54	37.48
0.15	5.54	6.28	7.06	7.90	9.84	12.28	15.37	19.43	25.11	31.36	32.47	33.53	34.55	35.56	36.54	37.48
0.16	5.16	5.83	6.53	7.28	8.98	11.06	13.61	16.79	20.98	26.91	32.47	33.53	34.55	35.56	36.54	37.48
0.17	4.83	5.45	6.08	6.77	8.29	10.10	12.27	14.89	18.19	22.58	28.68	33.53	34.55	35.56	36.54	37.48
0.18	4.54	5.12	5.71	6.33	7.71	9.33	11.22	13.45	16.16	19.63	24.17	30.29	34.55	35.56	36.54	37.48
0.19	4.29	4.83	5.38	5.96	7.22	8.68	10.37	12.31	14.62	17.48	21.07	25.66	31.87	35.56	36.54	37.48
0.20	4.07	4.57	5.09	5.63	6.80	8.14	9.66	11.39	13.40	15.83	18.79	22.43	27.12	33.53	36.54	37.48
0.21	3.87	4.35	4.83	5.34	6.44	7.67	9.06	10.62	12.41	14.52	17.04	20.05	23.78	28.64	35.17	37.48
0.22	3.68	4.14	4.60	5.08	6.11	7.27	8.55	9.97	11.58	13.46	15.65	18.21	21.29	25.18	30.15	36.65
0.23	3.52	3.95	4.39	4.85	5.82	6.90	8.10	9.41	10.87	12.57	14.51	16.73	19.36	22.58	26.56	31.54
0.24	3.36	3.78	4.20	4.64	5.56	6.58	7.70	8.92	10.27	11.81	13.56	15.53	17.82	20.56	23.86	27.86
0.25	3.22	3.62	4.03	4.44	5.33	6.29	7.35	8.49	9.74	11.16	12.74	14.52	16.54	18.93	21.75	25.08
0.26	3.09	3.48	3.87	4.27	5.11	6.03	7.03	8.10	9.27	10.58	12.05	13.66	15.48	17.59	20.05	22.89
0.27	2.96	3.34	3.72	4.10	4.91	5.79	6.74	7.76	8.86	10.08	11.43	12.91	14.57	16.47	18.64	21.12
0.28	2.85	3.21	3.58	3.95	4.73	5.58	6.48	7.44	8.48	9.63	10.89	12.26	13.78	15.51	17.46	19.65
0.29	2.74	3.09	3.45	3.81	4.56	5.37	6.24	7.16	8.14	9.23	10.41	11.69	13.09	14.68	16.45	18.42
0.30	2.63	2.98	3.32	3.67	4.40	5.19	6.02	6.90	7.84	8.86	9.98	11.18	12.48	13.95	15.57	17.36
0.31	2.53	2.87	3.21	3.55	4.25	5.01	5.81	6.65	7.55	8.53	9.59	10.71	11.94	13.30	14.80	16.44
0.32	2.44	2.77	3.10	3.43	4.11	4.85	5.62	6.43	7.29	8.23	9.23	10.30	11.45	12.73	14.12	15.64
0.33	...	2.67	2.99	3.32	3.98	4.70	5.44	6.22	7.05	7.95	8.91	9.92	11.01	12.21	13.52	14.92
0.34	...	2.58	2.89	3.21	3.86	4.55	5.28	6.03	6.83	7.69	8.61	9.57	10.61	11.74	12.97	14.28

Table 3-12 Values of L for Pipe Sizes \geq NPS 56 Through NPS 60 (Cont'd)

Depth, <i>d</i> , in.	Wall Thickness, <i>t</i> , in.															
	0.406	0.438	0.469	0.500	0.562	0.625	0.688	0.750	0.812	0.875	0.938	1.000	1.062	1.125	1.188	1.250
0.35	...	2.49	2.80	3.11	3.74	4.42	5.12	5.85	6.62	7.45	8.33	9.25	10.24	11.31	12.47	13.71
0.36	2.70	3.01	3.63	4.29	4.97	5.68	6.43	7.22	8.07	8.96	9.90	10.92	12.02	13.19
0.37	2.62	2.92	3.52	4.17	4.83	5.52	6.24	7.01	7.83	8.68	9.58	10.56	11.61	12.72
0.38	2.83	3.42	4.05	4.70	5.37	6.07	6.82	7.61	8.43	9.29	10.23	11.23	12.28
0.39	2.74	3.33	3.94	4.57	5.23	5.91	6.63	7.40	8.19	9.02	9.92	10.88	11.88
0.40	2.66	3.23	3.83	4.45	5.09	5.75	6.46	7.20	7.96	8.77	9.63	10.55	11.51
0.41	3.14	3.73	4.34	4.96	5.61	6.29	7.01	7.75	8.53	9.37	10.25	11.17
0.42	3.06	3.63	4.23	4.84	5.47	6.14	6.83	7.55	8.31	9.11	9.97	10.85
0.43	2.97	3.54	4.13	4.72	5.34	5.99	6.67	7.37	8.10	8.88	9.70	10.55
0.44	2.89	3.45	4.02	4.61	5.21	5.85	6.51	7.19	7.90	8.66	9.45	10.27
0.45	3.36	3.93	4.50	5.09	5.71	6.36	7.02	7.71	8.45	9.22	10.01
0.46	3.28	3.83	4.39	4.97	5.58	6.21	6.86	7.53	8.25	8.99	9.76
0.47	3.20	3.74	4.29	4.86	5.46	6.07	6.71	7.36	8.06	8.78	9.53
0.48	3.12	3.66	4.20	4.75	5.34	5.94	6.56	7.20	7.88	8.58	9.31
0.49	3.04	3.57	4.11	4.65	5.22	5.82	6.42	7.05	7.71	8.39	9.10
0.50	2.97	3.49	4.02	4.55	5.12	5.70	6.29	6.90	7.54	8.21	8.90
0.51	3.41	3.93	4.46	5.01	5.58	6.16	6.76	7.39	8.04	8.71
0.52	3.34	3.85	4.37	4.91	5.47	6.03	6.62	7.24	7.88	8.53
0.53	3.26	3.76	4.28	4.81	5.36	5.92	6.49	7.09	7.72	8.36
0.54	3.19	3.69	4.19	4.72	5.26	5.80	6.37	6.96	7.57	8.19
0.55	3.12	3.61	4.11	4.62	5.15	5.69	6.25	6.83	7.43	8.04
0.56	3.53	4.02	4.53	5.06	5.59	6.13	6.70	7.29	7.88
0.57	3.46	3.95	4.45	4.96	5.48	6.02	6.58	7.15	7.74
0.58	3.39	3.87	4.37	4.87	5.38	5.91	6.46	7.02	7.60
0.59	3.32	3.79	4.28	4.78	5.29	5.80	6.34	6.90	7.46
0.60	3.25	3.72	4.20	4.70	5.19	5.70	6.23	6.78	7.33
0.61	3.65	4.13	4.61	5.10	5.60	6.13	6.66	7.21
0.62	3.58	4.05	4.53	5.02	5.51	6.02	6.55	7.09
0.63	3.51	3.98	4.45	4.93	5.42	5.92	6.44	6.97
0.64	3.45	3.91	4.38	4.85	5.33	5.83	6.34	6.86
0.65	3.84	4.30	4.77	5.24	5.73	6.24	6.75
0.66	3.77	4.23	4.69	5.16	5.64	6.14	6.64
0.67	3.71	4.16	4.61	5.07	5.55	6.04	6.54
0.68	3.64	4.09	4.54	4.99	5.47	5.95	6.44
0.69	3.58	4.02	4.46	4.92	5.38	5.86	6.34
0.70	3.51	3.95	4.39	4.84	5.30	5.77	6.24

Table 3-12 Values of L for Pipe Sizes \geq NPS 56 Through NPS 60 (Cont'd)

Depth, <i>d</i> , in.	Wall Thickness, <i>t</i> , in.															
	0.406	0.438	0.469	0.500	0.562	0.625	0.688	0.750	0.812	0.875	0.938	1.000	1.062	1.125	1.188	1.250
0.71	3.89	4.32	4.76	5.22	5.69	6.15
0.72	3.83	4.26	4.69	5.14	5.60	6.06
0.73	3.76	4.19	4.62	5.07	5.52	5.98
0.74	3.70	4.12	4.55	4.99	5.44	5.89
0.75	3.64	4.06	4.48	4.92	5.36	5.81
0.76	4.00	4.42	4.85	5.29	5.73
0.77	3.94	4.35	4.78	5.21	5.65
0.78	3.87	4.29	4.71	5.14	5.57
0.79	3.82	4.22	4.64	5.07	5.49
0.80	3.76	4.16	4.58	5.00	5.42
0.81	4.10	4.51	4.93	5.35
0.82	4.04	4.45	4.86	5.28
0.83	3.98	4.39	4.80	5.21
0.84	3.93	4.33	4.73	5.14
0.85	4.27	4.67	5.07
0.86	4.21	4.61	5.01
0.87	4.15	4.55	4.94
0.88	4.10	4.49	4.88
0.89	4.04	4.43	4.82
0.90	3.99	4.37	4.76
0.91	4.32	4.70
0.92	4.26	4.64
0.93	4.20	4.58
0.94	4.15	4.52
0.95	4.10	4.47
0.96	4.41
0.97	4.36
0.98	4.31
0.99	4.25
1.00	4.20

Table 3-12M Values of L for Pipe Sizes ≥ 1 422 mm Through 1 524 mm O.D.

Depth, <i>d</i> , mm	Wall Thickness, <i>t</i> , mm															
	10.3	11.1	11.9	12.7	14.3	15.9	17.5	19.1	20.6	22.2	23.8	25.4	27.0	28.6	30.2	31.8
1.0	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
1.3	542.6	563.6	583.2	602.1	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
1.5	542.6	563.6	583.2	602.1	638.4	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
1.8	542.6	563.6	583.2	602.1	638.4	673.2	706.3	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
2.0	376.8	485.4	583.2	602.1	638.4	673.2	706.3	737.5	No limit	No limit	No limit	No limit	No limit	No limit	No limit	No limit
2.3	290.3	353.8	434.2	544.1	638.4	673.2	706.3	737.5	767.3	796.5	No limit	No limit	No limit	No limit	No limit	No limit
2.5	240.7	285.1	337.6	402.9	600.1	673.2	706.3	737.5	767.3	796.5	824.7	851.5	No limit	No limit	No limit	No limit
2.8	207.9	242.3	281.1	327.0	450.9	658.2	706.3	737.5	767.3	796.5	824.7	851.5	877.5	No limit	No limit	No limit
3.0	184.4	212.6	243.5	278.9	368.4	500.5	706.3	737.5	767.3	796.5	824.7	851.5	877.5	903.2	928.1	No limit
3.3	166.5	190.5	216.3	245.3	315.4	411.1	549.1	737.5	767.3	796.5	824.7	851.5	877.5	903.2	928.1	952.1
3.6	152.3	173.3	195.7	220.2	278.0	353.0	453.5	594.0	767.3	796.5	824.7	851.5	877.5	903.2	928.1	952.1
3.8	140.7	159.5	179.2	200.7	250.1	311.8	390.5	493.4	637.9	796.5	824.7	851.5	877.5	903.2	928.1	952.1
4.1	131.0	148.1	165.8	185.0	228.2	280.8	345.6	426.4	532.8	683.6	824.7	851.5	877.5	903.2	928.1	952.1
4.3	122.6	138.3	154.6	171.9	210.5	256.5	311.7	378.1	461.9	573.6	728.4	851.5	877.5	903.2	928.1	952.1
4.6	115.4	130.0	144.9	160.8	195.9	236.9	285.0	341.6	410.5	498.7	614.0	769.4	877.5	903.2	928.1	952.1
4.8	109.0	122.7	136.6	151.3	183.5	220.6	263.4	312.7	371.4	444.0	535.2	651.7	809.5	903.2	928.1	952.1
5.1	103.3	116.2	129.3	143.0	172.8	206.8	245.4	289.2	340.4	402.2	477.4	569.8	688.8	851.7	928.1	952.1
5.3	98.2	110.4	122.7	135.7	163.5	194.9	230.2	269.7	315.1	368.9	432.9	509.2	603.9	727.5	893.2	952.1
5.6	93.6	105.2	116.9	129.1	155.2	184.5	217.1	253.2	294.1	341.8	397.5	462.4	540.8	639.5	765.7	930.8
5.8	89.3	100.4	111.6	123.2	147.9	175.4	205.7	238.9	276.2	319.2	368.5	425.0	491.8	573.6	674.7	801.2
6.1	85.4	96.1	106.7	117.8	141.3	167.2	195.7	226.5	260.8	299.9	344.3	394.4	452.5	522.2	606.2	707.8
6.4	81.8	92.0	102.3	112.9	135.3	159.9	186.7	215.5	247.4	283.3	323.7	368.7	420.2	480.9	552.5	637.0
6.6	78.4	88.3	98.2	108.4	129.8	153.2	178.6	205.8	235.5	268.9	306.0	346.9	393.1	446.9	509.3	581.4
6.9	75.3	84.8	94.4	104.2	124.8	147.2	171.3	197.0	224.9	256.1	290.4	328.0	370.0	418.3	473.6	536.5
7.1	72.3	81.6	90.8	100.3	120.1	141.6	164.6	189.0	215.4	244.7	276.7	311.5	350.0	393.9	443.5	499.2
7.4	69.5	78.5	87.5	96.7	115.8	136.5	158.5	181.8	206.8	234.4	264.5	296.9	332.5	372.8	417.8	467.8
7.6	66.8	75.7	84.4	93.3	111.8	131.7	152.9	175.1	199.0	225.2	253.5	283.8	317.1	354.2	395.5	440.9
7.9	64.3	72.9	81.4	90.1	108.1	127.3	147.7	169.0	191.8	216.7	243.5	272.1	303.3	337.9	376.0	417.6
8.1	61.9	70.3	78.6	87.1	104.5	123.1	142.8	163.4	185.2	209.0	234.5	261.6	290.9	323.2	358.7	397.1
8.4	...	67.9	76.0	84.2	101.2	119.3	138.3	158.1	179.1	201.9	226.2	251.9	279.6	310.1	343.3	379.0
8.6	...	65.5	73.4	81.5	98.0	115.6	134.1	153.2	173.4	195.3	218.6	243.1	269.4	298.2	329.4	362.8

Table 3-12M Values of L for Pipe Sizes ≥ 1 422 mm Through 1 524 mm O.D. (Cont'd)

Depth, d, mm	Wall Thickness, t, mm															
	10.3	11.1	11.9	12.7	14.3	15.9	17.5	19.1	20.6	22.2	23.8	25.4	27.0	28.6	30.2	31.8
8.9	...	63.3	71.0	78.9	95.1	112.2	130.1	148.6	168.2	189.2	211.5	235.0	260.0	287.4	316.8	348.2
9.1	68.7	76.4	92.2	108.9	126.3	144.3	163.2	183.5	205.0	227.5	251.4	277.4	305.4	335.0
9.4	66.5	74.1	89.5	105.8	122.8	140.2	158.5	178.2	198.9	220.5	243.4	268.3	294.9	323.0
9.7	71.8	86.9	102.8	119.4	136.4	154.2	173.2	193.2	214.0	236.0	259.8	285.2	312.0
9.9	69.6	84.5	100.0	116.2	132.7	150.0	168.5	187.8	207.9	229.2	252.0	276.3	301.8
10.2	67.5	82.1	97.3	113.1	129.3	146.1	164.0	182.8	202.2	222.7	244.7	268.0	292.4
10.4	79.8	94.8	110.2	126.0	142.4	159.8	178.1	196.9	216.7	237.9	260.3	283.7
10.7	77.6	92.3	107.4	122.9	138.9	155.8	173.6	191.8	211.0	231.5	253.1	275.6
10.9	75.5	89.9	104.8	119.9	135.5	152.1	169.3	187.1	205.7	225.5	246.4	268.1
11.2	73.5	87.6	102.2	117.0	132.3	148.5	165.3	182.6	200.6	219.9	240.1	261.0
11.4	85.4	99.8	114.3	129.2	145.0	161.5	178.3	195.8	214.5	234.1	254.3
11.7	83.3	97.4	111.6	126.3	141.8	157.8	174.2	191.3	209.4	228.4	248.0
11.9	81.3	95.1	109.1	123.5	138.6	154.3	170.3	187.0	204.6	223.1	242.1
12.2	79.3	92.9	106.6	120.8	135.6	150.9	166.6	182.9	200.1	218.0	236.5
12.4	77.3	90.8	104.3	118.2	132.7	147.7	163.1	179.0	195.7	213.2	231.2
12.7	75.4	88.7	102.0	115.7	129.9	144.7	159.7	175.2	191.6	208.6	226.1
13.0	86.7	99.8	113.2	127.3	141.7	156.4	171.6	187.6	204.3	221.3
13.2	84.8	97.7	110.9	124.7	138.9	153.3	168.2	183.8	200.1	216.7
13.5	82.9	95.6	108.6	122.2	136.1	150.3	164.9	180.2	196.1	212.3
13.7	81.0	93.6	106.4	119.8	133.5	147.4	161.7	176.7	192.3	208.1
14.0	79.2	91.7	104.3	117.4	130.9	144.6	158.6	173.4	188.6	204.1
14.2	89.8	102.2	115.2	128.5	141.9	155.7	170.1	185.1	200.3
14.5	87.9	100.2	113.0	126.1	139.3	152.8	167.0	181.7	196.6
14.7	86.1	98.3	110.9	123.8	136.7	150.1	164.0	178.4	193.0
15.0	84.4	96.4	108.8	121.5	134.3	147.4	161.1	175.3	189.6
15.2	82.7	94.5	106.8	119.3	131.9	144.9	158.3	172.2	186.3
15.5	92.7	104.9	117.2	129.6	142.4	155.6	169.3	183.1
15.7	91.0	103.0	115.2	127.4	140.0	153.0	166.4	180.0
16.0	89.3	101.1	113.1	125.2	137.6	150.5	163.7	177.0
16.3	87.6	99.3	111.2	123.1	135.3	148.0	161.0	174.2
16.5	97.5	109.3	121.1	133.1	145.6	158.4	171.4
16.8	95.8	107.4	119.1	131.0	143.3	155.9	168.7
17.0	94.1	105.6	117.1	128.9	141.0	153.5	166.0
17.3	92.5	103.9	115.2	126.8	138.8	151.1	163.5
17.5	90.9	102.1	113.4	124.8	136.7	148.8	161.0
17.8	89.3	100.4	111.6	122.9	134.6	146.6	158.6

Table 3-12M Values of L for Pipe Sizes ≥ 1 422 mm Through 1 524 mm O.D. (Cont'd)

Depth, d , mm	Wall Thickness, t , mm															
	10.3	11.1	11.9	12.7	14.3	15.9	17.5	19.1	20.6	22.2	23.8	25.4	27.0	28.6	30.2	31.8
18.0	98.8	109.8	121.0	132.6	144.4	156.3
18.3	97.2	108.1	119.2	130.6	142.3	154.0
18.5	95.6	106.4	117.3	128.7	140.2	151.8
18.8	94.0	104.7	115.6	126.8	138.2	149.6
19.1	92.5	103.1	113.8	124.9	136.2	147.5
19.3	101.5	112.2	123.1	134.3	145.4
19.6	100.0	110.5	121.4	132.4	143.4
19.8	98.4	108.9	119.6	130.5	141.5
20.1	96.9	107.3	117.9	128.7	139.6
20.3	95.4	105.7	116.3	127.0	137.7
20.6	104.2	114.6	125.2	135.8
20.8	102.7	113.0	123.5	134.0
21.1	101.2	111.5	121.9	132.3
21.3	99.7	109.9	120.2	130.5
21.6	108.4	118.6	128.8
21.8	106.9	117.1	127.2
22.1	105.5	115.5	125.6
22.4	104.0	114.0	124.0
22.6	102.6	112.5	122.4
22.9	101.2	111.1	120.8
23.1	109.6	119.3
23.4	108.2	117.8
23.6	106.8	116.4
23.9	105.4	114.9
24.1	104.1	113.5
24.4	112.1
24.6	110.7
24.9	109.4
25.1	108.0
25.4	106.7

ASME CODE FOR PRESSURE PIPING, B31

Power Piping	B31.1-2007
Fuel Gas Piping	B31.2 ¹ -1968
Process Piping	B31.3-2008
Pipeline Transportation Systems for Liquid Hydrocarbons and Other Liquids	B31.4-2006
Refrigeration Piping and Heat Transfer Components	B31.5-2006
Gas Transmission and Distribution Piping Systems	B31.8-2007
Managing System Integrity of Gas Pipelines	B31.8S-2004
Building Services Piping	B31.9-2008
Slurry Transportation Piping Systems	B31.11-2002
Hydrogen Piping and Pipelines	B31.12-2008
Standard for the Seismic Design and Retrofit of Above-Ground Piping Systems	B31E-2008
Manual for Determining the Remaining Strength of Corroded Pipelines: Supplement to ASME B31 Code for Pressure Piping.	B31G-2009
Standard Test Method for Determining Stress Intensification Factors (<i>i</i> -Factors) for Metallic Piping Components	B31J-2008
Pipeline Personnel Qualification	B31Q-2006

NOTE:

(1) USAS B31.2-1968 was withdrawn as an American National Standard on February 18, 1988. ASME will continue to make available USAS B31.2-1968 as a historical document for a period of time.

The ASME Publications Catalog shows a complete list of all the Standards published by the Society. For a complimentary catalog, or the latest information about our publications, call 1-800-THE-ASME (1-800-843-2763).

ASME Services

ASME is committed to developing and delivering technical information. At ASME's Information Central, we make every effort to answer your questions and expedite your orders. Our representatives are ready to assist you in the following areas:

ASME Press	Member Services & Benefits	Public Information
<i>Codes & Standards</i>	Other ASME Programs	Self-Study Courses
Credit Card Orders	Payment Inquiries	Shipping Information
IMEchE Publications	Professional Development	Subscriptions/Journals/Magazines
Meetings & Conferences	Short Courses	Symposia Volumes
Member Dues Status	Publications	Technical Papers

How can you reach us? It's easier than ever!

There are four options for making inquiries* or placing orders. Simply mail, phone, fax, or E-mail us and an Information Central representative will handle your request.

<i>Mail</i>	<i>Call Toll Free</i>	<i>Fax—24 hours</i>	<i>E-Mail—24 hours</i>
ASME	US & Canada: 800-THE-ASME	973-882-1717	Infocentral@asme.org
22 Law Drive, Box 2900	(800-843-2763)	973-882-5155	
Fairfield, New Jersey	Mexico: 95-800-THE-ASME		
07007-2900	(95-800-843-2763)		
	Universal: 973-882-1167		

* Information Central staff are not permitted to answer inquiries about the technical content of this code or standard. Information as to whether or not technical inquiries are issued to this code or standard is shown on the copyright page. All technical inquiries must be submitted in writing to the staff secretary. Additional procedures for inquiries may be listed within.

INTENTIONALLY LEFT BLANK

ASME B31G-2009

ISBN-13 : 978-0-7918-3261-5
ISBN-10 : 0-7918-3261-9



9 780791 832615



A12109